BNL-113651-2017-JA

Importance of Low Dimensional CeO_x Nanostructures in Pt/CeO_x-TiO₂ Catalysts for the Water-Gas Shift Reaction

**Si Luo, Laura Barrio, Thuy-Duong Nguyen-Phan, Dimitriy Vovchok,
Aaron C. Johnston-Peck, Wenqian Xu, Eric A. Stach,
and José A. Rodriguez, and Sanjaya D. Senanayake**

Submitted to JPCC

March 2017

Chemistry Department

Brookhaven National Laboratory

**U.S. Department of Energy
USDOE Office of Science (SC),
Basic Energy Sciences (BES) (SC-22)**

Notice: This manuscript has been authored by employees of Brookhaven Science Associates, LLC under Contract No. DE- SC0012704 with the U.S. Department of Energy. The publisher by accepting the manuscript for publication acknowledges that the United States Government retains a non-exclusive, paid-up, irrevocable, world-wide license to publish or reproduce the published form of this manuscript, or allow others to do so, for United States Government purposes.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or any third party's use or the results of such use of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Importance of Low Dimensional CeO_x Nanostructures in Pt/CeO_x-TiO₂ Catalysts for the Water-Gas Shift Reaction

Si Luo,^{a,d} Laura Barrio,^b Thuy-Duong Nguyen-Phan,^a Dimitriy Vovchok,^{a,d} Aaron C. Johnston-Peck,^c
Wenqian Xu,^a Eric A. Stach,^c and José A. Rodriguez,^{a,d} and Sanjaya D. Senanayake^{a*}

^a Chemistry Department, Brookhaven National Laboratory, Upton, NY 11973, USA.

^b CSIC - Instituto de Catalisis y Petroleoquimica, Cantoblanco, E-28049-Madrid, Spain

^c Center for Functional Nanomaterials, Brookhaven National Laboratory, Upton, NY 11973, USA.

^d Department of Chemistry, Stony Brook University, Stony Brook, NY 11794, USA

Email: [*ssenanay@bnl.gov](mailto:ssenanay@bnl.gov)

Abstract

CO₂ and H₂ production from the water-gas shift (WGS) reaction was studied over Pt/CeO_x-TiO₂ catalysts with incremental loadings of CeO_x, that adopts variations in the local morphology. The lowest loading of CeO_x (1 wt% ~ 0.5 at%) that is configured in its smallest dimensions exhibited the best WGS activity over larger dimensional structures. We attribute this to several factors including the ultrafine dispersed one-dimensional nanocluster geometry, a large concentration of Ce³⁺ and enhanced reducibility of the low loadings. We utilized several in situ experiments to monitor the active state of the catalyst during the WGS reaction. X-ray diffraction (XRD) results showed lattice expansion that indicated reduced ceria was prevalent during the WGS reaction. On the surface, Ce³⁺ related hydroxyl groups were identified by diffuse reflectance infrared Fourier-transform spectroscopy (DRIFTS). The enhanced reducibility of the catalyst with the introduction of ceria was further revealed by H₂-temperature programmed reduction (H₂-TPR) and good thermal stability was confirmed by *in situ* environmental transmission electron microscopy (ETEM). We also investigated the formation of the low dimensional structures during catalyst preparation, through a two-stage crystal growth of ceria crystallite on TiO₂ nanoparticle: fine crystallites ~1D formed at ~250 °C, followed by crystal growth into 2D chain and 3D particle from 250~400 °C.

INTRODUCTION

The water-gas shift reaction ($\text{CO} + \text{H}_2\text{O} \rightarrow \text{H}_2 + \text{CO}_2$) is one of the most important industrial catalytic processes for clean H_2 production and purification.¹⁻⁷ The common industrial catalysts used for the WGS reaction are pyrophoric, *i.e.* mixtures of Fe-Cr or Zn-Al-Cu oxides, and require lengthy and complex activation steps before usage.⁴ Several classes of novel, active catalysts have been recently developed to improve performance and stability: Model and powder catalysts in which noble metals (Au, Pt, Ru) are supported on plain metal oxides (CeO_2 , TiO_2 , ZrO_2 , CuO, ZnO, SiO_2), transition metal (Ni, W, Ce, Cu) doped oxides, and mixed metal oxides (CeO_2 - TiO_2 , CuO- CeO_2 , CeO_2 - ZrO_2).¹⁻¹⁶

Among them, ceria based materials are one of the most promising WGS components owing to the inherent $\text{Ce}^{4+}/\text{Ce}^{3+}$ redox cycle, oxygen storage capability and excellent thermal / chemical stability.^{1,5,6,8,9,11-14} CeO_2 nanoparticles with a mean size less than 10 nm exhibit quantum confinement effect and significant cell parameter enlargement due to large quantity of Ce^{3+} centers and consequent formation of oxygen vacancy defects.^{17,18} It is noteworthy that the addition of Pt nanoparticles on CeO_2 significantly improve the WGS activity *via* a redox mechanism in which reduced platinum interacts with CO whereas partially reduced CeO_x species dissociate water.¹³ It has been proven that the catalytic behavior of CeO_2 for the WGS reaction could be enhanced by the presence of second oxide as a substrate, *i.e.* TiO_2 , so that the size, dispersion and surface properties of CeO_2 can be successfully controlled.^{6,13} Jose. J. Plata¹⁴ et al. reported the synergistic effects at the metal oxide interface in Cu/ CeO_x - TiO_2 (110) system and illustrates the importance of the phase of CeO_x to promote the WGS catalytic performance. Pt/ CeO_x - TiO_2 was found to have improved WGS activity at a loading of 6 wt% of CeO_x on TiO_2 because it facilitated the dispersion of small particles of Pt and improved the reducibility of the ceria component at low temperatures.¹³ Recently, we have identified the crucial role of hierarchical heterogeneity at the CeO_x - TiO_2 interface in H_2 and O_2 evolution from water photocatalytic splitting. CeO_x distributed on the anatase TiO_2 support in different geometries according

to its loading content: Ultrafine dispersed one-dimensional (1D) clusters smaller than 1 nm (1 wt%), additional two-dimensional (2D) trapezoidal chains and short islands (3 wt%), and additional large three-dimensional (3D) hemispherical nanoparticles (6 wt%). We have demonstrated that a low dimensional geometry of CeO_x with enriched Ce³⁺ concentration at the CeO_x surface and at the CeO_x-TiO₂ interface provided unique electronic and geometrical properties that are beneficial to the photocatalytic activity.¹⁹

Therefore, inspired from our previous work, we report herein the use of Pt/CeO_x-TiO₂ as a catalyst for the WGS reaction with the aim of further elucidate the importance of the CeO_x structure. We investigate the crucial role of CeO_x dimensions and geometry in correlation to the WGS activity by *in situ* XRD and DRIFTS under reaction conditions. The catalyst reducibility is probed by H₂-TPR and thermal stability of morphological structure is proved by *in situ* environmental TEM. The crystal growth of CeO_x on TiO₂ support is further investigated by means of TGA/DTA, time-resolved *in situ* XRD, PDF and scanning TEM (STEM).

EXPERIMENTAL

Catalyst preparation

CeO_x-TiO₂ samples using commercial anatase TiO₂ nanoparticles were synthesized by wet impregnation method using cerium nitrate precursor, and labeled as xCeTi with x = 1, 3, and 6 wt% CeO_x (nominal contents, *as-impregnated* samples). Subsequently, CeO_x-TiO₂ catalysts were calcined to 500 °C, prior to being loaded with 0.5 wt% Pt from H₂PtCl₆ solution by wet impregnation route and denoted as PtxCeTi (where x = 1, 3, and 6 wt% CeO₂). The experimental details were described in previous report.¹⁹

***Ex situ* characterization**

Annular dark-field scanning transmission electron microscopy (STEM) images and energy electron loss spectra (EELS) were collected with an aberration-corrected Hitachi HD-2700C operating at an accelerating voltage of 200 kV and using a probe convergence semi-angle of 23 mrad. The inner collection angle of the annular dark field detector was approximately 53 mrad while the collection angle for energy electron loss spectroscopy was 20 mrad.

***In situ* characterization during thermal treatment**

Thermogravimetric analysis (TGA) and differential thermal analysis (DTA) were performed on a Mettler Toledo TGA/SDTA 851 apparatus. Typically, 30–40 mg of the powder catalyst were heated from 298 to 1373 K at a rate of 10 K min⁻¹ under air and 10% H₂/N₂ atmospheres.

In situ time-resolved X-ray diffraction (TR-XRD) patterns and atomic pair distribution function (PDF) profiles were collected at beamline X7B ($\lambda = 0.3196 \text{ \AA}$) of the National Synchrotron Light Source (NSLS) at BNL. 5 mg of powder were loaded into a quartz capillary mounted on a Clausen flow cell. *As-prepared* CeO_x-TiO₂ samples were heated at 10 °C min⁻¹ from 25 to 600 °C under O₂ atmosphere. Experiment details were described elsewhere.¹² The Rietveld refinement was conducted by using the General Structure Analysis System II (GSAS II) software.²⁰

In situ environmental transmission electron microscopy (ETEM) images were recorded on an aberration-corrected FEI Titan 80-300 operating at 300 kV. STEM and ETEM characterizations were conducted at the CFN-BNL. The 6 wt% CeO_x-TiO₂ sample was imaged under $\sim 1.1 \times 10^{-3}$ torr H₂ at elevated temperatures: 100 °C, 200 °C and 300 °C, using a furnace-type heating holder (Gatan, Inc.).

H₂-temperature programmed reduction (H₂-TPR) of the calcined samples was carried out using a Micromeritics 2900 instrument in a U-shaped quartz reactor. Prior to the reduction test, 30 mg of powder were flushed with Helium at 150 °C for 15 min and then cooled down to room temperature.

TPR profiles were obtained by heating the sample under a 10 % H₂/Ar flow (50 mL min⁻¹) from 25 °C to 900 °C at a linearly programmed rate of 10 °C min⁻¹.

***In situ* Diffuse Reflectance Infrared Fourier Transform Spectroscopy (DRIFTS) and WGS activity**

In situ DRIFTS data of PtCeTi samples under WGS reaction condition were collected on a Bruker Equinox 55 FTIR spectrometer equipped with a modified Harrick Praying Mantis DRIFT cell. 5% CO/He was monitored by a calibrated flow meter with the flow rate of 20 mL min⁻¹ and mixed with ~3% water vapour by passing through a water bubbler. The system was stabilized at each elevated temperature step for 30 min and then 516 scans were collected to improve the signal to noise ratio. Instrument details could be found in previous report.²⁰

***In situ* X-ray Diffraction and WGS activity**

In situ XRD experiments were carried out at beamline 17BM-B of the Advanced Photon Source at Argonne National Laboratory under WGS reaction condition. 10mg of powder sample was loaded into a 1.1mm OD, 0.9 mm ID quartz capillary mounted onto a Clausen microflow reactor cell. The WGS reactant gas mixture (5% CO, 3% H₂O from bubbler, balance Helium) was introduced to the reactor at a flow rate of 20 scc per min. The sample was heated and cooled stepwise under reactant gas flow at a rate of 5°C/min up to 400°C and subsequently cool down to room temperature. Diffraction data was collected continuously throughout the process, and product gas outflow was analyzed using an RGA 300 quadrupole mass spectrometer system. The phase composition and lattice parameters were also analyzed by Rietveld refinement using the General Structure Analysis System II (GSAS II) software.²⁰

RESULTS AND DISCUSSION

Structure evolution of CeO_x-TiO₂ during oxidative annealing

The thermal behavior of the mixed metal oxide systems was studied by TGA/DTA analysis. **Fig. 1** shows the compositional change of *as-impregnated* CeTi samples as a function of CeO_x loading in air. Four distinct stages can be seen in TGA/DTA curves as annealing in air although different CeO_x loadings reveal different behaviors. The total weight loss occurs remarkably in *as-impregnated* 3CeTi and 6CeTi, about 4.5% and 9.5%, respectively. The first weight loss below 170 °C is attributed to the removal of moisture residue and trapped CO₂. The major weight loss associated with a large endothermal DTA peak takes place between 175 and 250 °C, possibly stemming from the removal of structural hydroxyl groups and the release of NO_x from the decomposition of nitrates from cerium precursors. This peak becomes sharp and intense in 6CeTi due to higher concentration of cerium precursors. Much smaller endothermic peak locates between 250 and 400 °C with less mass loss might be ascribed to the crystallization of amorphous and/or cerium hydroxide and the oxidation of Ce³⁺ to Ce⁴⁺. No significant weight loss was found beyond 400 °C until 720 °C where the anatase-to-rutile phase transformation of TiO₂ occurs. It indicates that the presence of CeO_x remarkably inhibits the phase transformation of the support that starts at 600 °C.

Figure 1. TGA (top) and DTA (bottom) analysis of *as-impregnated* xCeTi samples in air.

The morphology evolution of a representative CeO_x-TiO₂ sample was also studied by means of electron microscopy. **Fig. 2** shows the STEM image of *as-impregnated* 6CeTi and its corresponding elemental mapping, confirming that the cerium species were well dispersed on the TiO₂ support. After annealing in O₂ to 600 °C, crystalline ceria was generated on the surface of TiO₂ while liberating H₂O. (STEM images after annealing were present in our previous work in reference¹⁹)

Figure 2. (A) STEM elemental map of *as-impregnated* 6 wt% $\text{CeO}_x\text{-TiO}_2$ and (B) schematic illustration describes the crystal growth of CeO_2 onto TiO_2 upon calcination.

In order to understand the growth mechanism of crystalline CeO_2 on TiO_2 surface, *in situ* XRD and PDF analysis were employed to provide more detailed studies. **Fig. 3(A)** displays the time-resolved XRD spectra for *as-impregnated* 6CeTi sample at different annealing temperatures. The crystallization of the ceria structure follows the process:

It can be seen that there was no crystalline CeO_2 features until annealing at 200 °C. A small and broadened peak in the range of ~ 5.5 to 6° , representative of amorphous phase, emerges at ~ 250 °C

which is consistent with the TGA/DTA result described above. This peak gradually grows and slightly shifts towards lower angle at ~ 400 °C. Such a growth obviously reveals the decomposition and crystallization of cubic fluorite CeO_2 (space group $Fm\bar{3}m$) from amorphous and/or $\text{Ce}(\text{OH})_3$ upon heat treatment. The reflection at 5.8° corresponding to CeO_2 [111] becomes sharper concomitantly with the adjunct appearance of [200] peak at 6.8° , as elevating the temperature beyond 400 °C. The evolution of CeO_2 particle size and Ce/Ti ratio obtained from sequential Rietveld refinement are presented in **Fig. 3(B)**. When temperature increases from 200 to ~ 450 °C, the particle size of ceria crystallites shows a tremendous increase from 3 nm to 6 nm. The CeO_2 fluorite-type structure is stabilized up to 600 °C with the average size of ~ 6.7 nm and a Ce/Ti ratio of 0.025 . An example of the XRD pattern fitting and analysis was included in supporting information (**Figure S1**).

Figure 3. (A) Time-resolved XRD spectra of as-impregnated 6CeTi sample, (B) Rietveld refinement of ceria as a function of temperature: particle size and Ce/Ti ratio.

The *in situ* XRD pattern shows the alteration in long-range crystal structure during the evolution of ceria crystallite. As a complementary investigation on the local atomic structure, we collected the total scattering to a large value of momentum transfer Q (~ 100). The real space atomic bond information

was obtained by using Python/PDFgetX3 program. $G(r)$ function defines the probability of finding a pair of atoms at a certain interatomic distance r , while the integrated intensity is related to the coherence scattering lengths and the multiplicities of the atom. **Fig. 4(A)** shows the comparison of PDF profiles of a CeO₂ nanoparticle standard, *as-impregnated* 6CeTi before calcination, during 600 °C *in situ* calcination and after calcination (cooling) in O₂ at 600 °C. The intense peaks at 1.96 Å and 3.05 Å are assigned to Ti-O and Ti-Ti pairs for the first neighbor coordination shell in [TiO₆] octahedral (the closet O shell around a Ti atom). The maximum at 3.83 Å is ascribed to the second asymmetric Ti-Ti/O-O coordination sphere. The line shape and peak position remain the same after annealing, indicating the stability of anatase TiO₂ during the ceria crystallization process. However, the noticeable enhancement in intensity of the peak at 3.83 Å after calcination can be due to the formation of Ce-Ce bonds during the crystallization of CeO₂, which are located at the same position. The two small peaks at 2.27 Å and 2.46 Å are ascribed to the Ce-O vector from CeO₂ and the O-O bond distance from TiO₂, respectively. The feature at 2.27 Å slightly shifts and broadens, compared to pure CeO₂, possibly due to the partial reduction of ceria at the CeO₂-TiO₂ interface and/or CeO₂ surface. As seen in the color contour map presenting the *in situ* time-resolved PDF during the calcination process (**Fig. 4(B)**), the intensity diminution of all the peaks at high temperature can be attributed to thermal effects. Afterwards, the intensity significantly increases after the cooling process comparing to the intensity before calcination, indicating the growth of CeO₂ fluorite-type structure in which the feature of Ce-O, Ce-Ce at 2.27 Å and 3.83 Å, respectively, can be taken into account.

Figure 4. *In situ* PDF analysis of *as-impregnated* 6CeTi sample during heat treatment from room temperature to 600 °C and then cooling down: (A) comparison of PDF profiles at different temperature: (B) color contour map of the full calcination process.

CeO_x-TiO₂ reducibility

Fig. 5 displays the H₂-TPR profiles where the hydrogen uptake as a function of temperature was plotted. TiO₂ and CeO_x-TiO₂ catalysts show two main asymmetric features in the range of 200-600 °C. It is obvious that the amount of H₂ consumption is proportional to CeO_x concentration, implying the

enhancement in surface reduction in the presence of CeO_x .²² The larger the H_2 consumption, the higher the surface oxygen concentration, indicating the significant reducibility of mixed oxide systems. In pure TiO_2 , the position of two poorly resolved reduction features with maxima at ~ 270 and 554 °C could be ascribed to the removal of loose capping oxygen and surface oxygen by H_2 .^{13,23} It has been reported that the reduction of CeO_2 involves two processes: the initial loss of surface oxygen at low temperature (~ 410 °C) and further removal of bulk oxygen at higher temperature (~ 510 °C).²² The reduction peak at low temperature obviously broadens and increases with increasing CeO_x content, probably due to the energetic differences of CeO_x dependent of the degree of interaction with the TiO_2 support.²² Since surface oxygen removal by H_2 began at 410 °C in pure CeO_2 ,²² small ceria structure supported on TiO_2 nanoparticles exhibit significant lower reduction temperature. The feature at high temperature with a left shoulder at ~ 500 °C becomes relatively intense and sharp, shifting downscale to 526 , 536 and 535 °C for 1CeTi , 3CeTi and 6CeTi , respectively, suggesting the reducibility of bulk and surface species on TiO_2 , and the concomitant reduction of cerium ions that might be related with easily removable surface oxygen from CeO_x entities in close contact with TiO_2 surface.^{13,23} Once Ce^{3+} species appear, the oxygen vacancy will be created to preserve the electrostatic balance. Since CeO_x in 1CeTi catalyst presents in a highly dispersed form with abundant Ce^{3+} and surface defects as shown in previous report,¹⁹ the reduction of either ceria or titania starts at lower temperature compared to others, therefore leading much better WGS performance compared to others. The reduction of both TiO_2 and CeO_x is consistent with the *in situ* XRD refinement aforementioned in which the ceria lattice parameter increases with raising temperature from 200 °C to 300 °C in reducing environment. The lattice expansion contributes to the structure distortion, leading to a high oxygen deficiency upon H_2 reduction. The *in situ* DRIFTS results are consistent with the H_2 -TPR profiles in which the reduction of bulk CeO_2 happens above 500 °C. It is noteworthy that the reducibility, which correlates with the oxygen storage capacity as well as $\text{Ce}^{4+} \rightleftharpoons \text{Ce}^{3+}$ and $\text{Ti}^{4+} \rightleftharpoons \text{Ti}^{3+}$ redox cycles, is significantly enhanced by adding small amount of ceria onto the titania support.²²

Figure 5. H₂-TPR profiles of TiO₂ standard and xCeTi samples.

On the other hand, we have directly observed the local morphological evolution of CeO_x-TiO₂ system under reactive environment by *in situ* imaging. **Fig. 6** shows the ETEM images of the 6CeTi sample annealed at 100, 200 and 300 °C in $\sim 1.1 \times 10^{-1}$ torr H₂. It can be seen that crystalline nanoparticles of CeO_x deposit onto TiO₂ support and the crystalline structure is retained with increasing temperature. A well-ordered structure of ceria in the atmosphere of H₂ at different temperatures strongly confirms the good stability of the 6CeTi sample under reducing condition. The electron microscopy images and H₂-TPR result are in agreement with our previous report that 6CeTi (Ce³⁺/Ce⁴⁺ atomic ratio of 0.28), shows lower reducibility at low temperature. It indicates that the CeO₂ and TiO₂ crystal structures are quite stable up to 300 °C in H₂.

Figure 6. *In situ* environmental TEM images of 6 wt% CeO_x-TiO₂ sample at 100, 200 and 300 °C in 1.1×10^{-1} torr H₂.

WGS activity study and structure change under reaction condition: *In situ* XRD and *in situ* DRIFTS

The catalytic WGS reaction on PtCeTi catalysts was monitored by *in situ* XRD and DRIFTS at different temperatures. As shown in **Fig. 7**, CO₂ product gas outflow analysis by RGA over 0.5% Pt loaded CeO_x-TiO₂ catalysts yields a clear trend in water-gas shift activity at different heating ramp temperatures as follows: 1% CeO_x > 3% CeO_x > 6% CeO_x. In contrast, plain TiO₂ and CeO_x-TiO₂ show no water-gas shift activity (not shown here). It may therefore be inferred from the crucial role of Pt on the CeO_x-TiO₂ support in activating these materials as water gas shift catalysts. As showed by STEM (**Figure S2**) Pt is dispersed on the surface of the material as nanoparticles with the size of 1~2 nm. The addition of Pt does not change the surface area of each catalyst as shown in supporting information (**Figure S3**). The Pt1CeTi system is the most active catalyst for WGS reaction regardless of the reaction temperature compared to others containing higher loading contents of CeO_x.

Figure 7. Water gas shift activity measured in a flow reactor by RGA during the water-gas shift reaction onto PtxCeTi series with different CeO_x loading and normalized to the surface area of the catalysts. (Original mass spectra measuring the partial pressure of CO₂ and H₂ were shown in the supporting information **Figure S4**)

Figure 8 (A) *In situ* XRD patterns of Pt3CeTi and Pt6CeTi catalysts under WGS reaction conditions as a function of temperature; (B) lattice parameter of CeO₂ sequentially refined from *in situ* XRD.

As reported previously,¹⁹ the anatase phase of the TiO₂ support was identified by synchrotron X-ray diffraction and X-ray absorption techniques together with small signals of CeO₂ fluorite-type structure at moderate to high loading content (3 and 6 wt%). After loading the Pt nanoparticles, the crystallographic phase of TiO₂ was unchanged. **Fig. 8(A)** shows *in situ* XRD pattern for the WGS reaction on the Pt6CeTi catalyst where numerous diffractions at $2\theta = 11.8, 17.5, 22.1$ and 24.6° were assigned to (101), (004), (200) and (105) plane of anatase TiO₂ (space group $I4_1/amd$); some small diffraction peaks at $2\theta = 13.4, 15.5$ and 25.8° were assigned to (111), (200) and (311) plane of cubic fluorite CeO₂ at room temperature. As the temperature increased under WGS reaction conditions, TiO₂ remained in the anatase phase up to 400 °C with no obvious change in the diffraction patterns. CeO₂ in its cubic fluorite phase was also observed during the process of the WGS reaction. The sequential Rietveld refinement analysis of fluorite-type CeO₂ for Pt loaded 3% and 6% CeO_x-TiO₂ catalysts obtained from *in situ* XRD patterns that were carried out under WGS reaction condition are plotted in

Fig. 8(B). Due to a very low loading, the refinement of the ceria lattice on the Pt1CeTi sample was impossible to conduct. The lattice parameters of CeO₂ on Pt3CeTi and Pt6CeTi at room temperature are 5.412 and 5.407 Å, respectively, which is consistent with the literature.^{17,24} Under WGS reaction conditions, thermal expansion of the lattice occurred in both catalysts²⁵ However, an abrupt expansion of the lattice was found at the temperature between 200°C and 250°C, suggesting the partial reduction of Ce⁴⁺ to Ce³⁺ and the consequential formation of oxygen vacancies.^{11,26,27} Such an extent of ceria reduction is bigger for Pt3CeTi possibly due to a lower particle size¹⁹ since the reduction of ceria strongly depends on the ceria crystallite size.²⁷ This expansion occurs concurrently with the initial observed water-gas shift activity. Similarly, a sharp contraction of the ceria lattice was observed as the temperature decreased from 200°C to 150°C upon cooling of the catalysts, indicating the oxidation of the ceria lattice. Thermal expansion of the TiO₂ cell (both a and c parameters) follow the normal evolution with temperature without the abrupt changes observed in the CeO₂, suggesting that no changes in the titania oxidation state occur during WGS reaction conditions.

Figure 9. *In situ* DRIFTS under WGS reaction conditions at different temperatures over Pt1CeTi, Pt3CeTi and Pt6CeTi catalysts

Fig. 9 shows *in situ* DRIFTS data for the WGS on Pt/CeO_x-TiO₂ samples with different CeO_x loadings. The similar surface species were observed for the three catalysts (shown in different panels from left to right) at each temperature step. At room temperature, a large broad band in the region of 3200 - 3700 cm⁻¹ accompanied with smaller band at 3660 cm⁻¹ are ascribed to the molecular adsorbed water and stretching vibration of surface doubly bridging hydroxyl groups, respectively.^{14,29-31} This band sharply decreases with increasing the temperature to 200 °C and completely disappears at higher temperature. Another small band at *ca.* 2345 cm⁻¹ corresponds to adsorbed CO₂. In the 2000-2300 cm⁻¹ region, a broad doublet centered at 2143 cm⁻¹ is present due to CO in the gas phase. As temperature increases to 200 °C, two peaks arise at 2060 cm⁻¹ and 2085 cm⁻¹, which are assigned to the strongly bound carbonyl species (*i.e.* bridging carbonyls) linearly adsorbed on metallic Pt and also to Pt-H stretching vibrations^{30,32} and these bands gradually diminish due to desorption at higher temperature. The doublet band at 2330 cm⁻¹ and 2360 cm⁻¹ grows up due to the production of gas phase CO₂ after a further increase of the temperature to 300 and 400 °C, indicating the facilitation of the WGS reaction.³³ Besides, a Fermi resonance doublet in the 2700-3000 cm⁻¹ region immersed in the water/OH bands shows up, indicating the presence of formate (HCOO⁻) species, in particular, $\nu(\text{C-H})$ stretching band at ~ 2940 cm⁻¹ and a combination $\delta(\text{C-H})$ bending mode and symmetric OCO stretches, $\nu_s(\text{OCO})$, ~ 2840 cm⁻¹.^{10,32} It has been reported that along with carbonate species, formate species are key intermediates in the WGS on ceria-based systems and formed by water dissociation with subsequent reaction of hydroxyl groups and CO.^{3,11,34,35} The formate bands vanish at 400 °C when the CO₂ production reaches the maximum. It is clear that much higher WGS activity was obtained at this temperature for all three catalysts; and both experimental and theoretical studies have recently demonstrated that the formate species are typically spectators and not truly intermediate species of the WGS mechanism.^{5,14,36,37} It can be concluded that the catalysts with different CeO_x concentration undergo the similar reaction pathway involving the formation of identical intermediate species adsorbed on the surface during the WGS reaction. Specifically, the formate bands appears at room temperature in Pt3CeTi and Pt6CeTi

catalysts and its intensity is proportional to the CeO_x loading content, suggesting the accumulation of formate species that is mostly accomplished by ceria on the surface. Otherwise, the doubly bridging hydroxyl groups at 3660 cm^{-1} in Pt6CeTi is more intense than in the others as the reaction temperature is increased to $400\text{ }^\circ\text{C}$, together with an emerging shoulder at $\sim 3730\text{ cm}^{-1}$, which is attributed to the single coordinated hydroxyl groups (type I, also OH unidentate) and bridging OH groups at oxygen vacancies.^{2,29,30,32} It is frequent that the bridging OH group associated with oxygen vacancies is dominant on reduced ceria surfaces while vertical OH on ceria is more intense on oxidized ceria. We have reported in a previous study that Pt6CeTi contains more oxidized ceria (Ce^{4+} states) whereas Pt1CeTi catalysts is highly dominated by Ce^{3+} .¹⁹ Ultrafine CeO_x clusters supported on TiO_2 could be easily reduced under WGS reaction condition, leading to the domination of reduced species and the highest WGS activity up to $400\text{ }^\circ\text{C}$; meanwhile, larger 3D CeO_2 particles on TiO_2 in Pt6CeTi could be partially reduced due to significant amount of bulk CeO_2 , resulting in lower activity.

CONCLUSIONS

We interrogated the importance of low dimensional CeO_x on the TiO_2 support in Pt/ CeO_x - TiO_2 catalysts for the WGS reaction using *in situ operando* XRD and DRIFTS studies. The two-stage crystal growth of ceria crystallite on TiO_2 nanoparticle: fine crystallite formed at $\sim 250\text{ }^\circ\text{C}$, followed by crystal growth into 2D chain and 3D particle from $250\sim 400\text{ }^\circ\text{C}$ growth process of ceria crystallite on TiO_2 nanoparticle was observed by means of TGA/DTA, time-resolved *in situ* XRD, PDF and STEM. As promising catalysts for WGS reaction, we also endeavored to prove the enhanced reducibility through H_2 -TPR and robust thermal stability by *in situ* environmental TEM. The catalyst involving ultrafine dispersed one-dimensional (1D) CeO_x clusters smaller than 1 nm exhibited the highest WGS activity and much enhanced reducibility, compared to the catalysts containing higher CeO_x loadings in higher dimensional geometries.

Supporting Information

The supporting information is available free of charge on the ACS Publications website at <http://pubs.acs.org>. This content includes several data sets including X-ray diffraction fitting of CeO_x-TiO₂ catalysts, STEM images of Pt particles in the Pt/CeO_x-TiO₂ catalysts, surface area comparisons between catalysts, and reactivity data of catalysts under reaction conditions.

Acknowledgements

This work was supported by the U.S. Department of Energy, Office of Science, Office of Basic Energy Sciences, and Catalysis Science Program under contract No. DE-SC0012704. This work used resources of the Center for Functional Nanomaterials (CFN), the National Synchrotron Light Source (NSLS) at BNL, and the Advanced Photon Source (17BM) of Argonne National Laboratory (No. DE-AC02-06CH11357) which are all DOE Office of Science User Facilities.

REFERENCES

1. Rodriguez, J. A.; Ma, S.; Liu, P.; Hrbek, J.; Evans, J.; Pérez, M. Activity of CeO_x and TiO_x Nanoparticles Grown on Au(111) in the Water-Gas Shift Reaction. *Science* **2007**, *318*, 1757-1760.
2. Meunier, F. C.; Goguet, A.; Hardacre, C.; Burch, R.; Thompsett, D. Quantitative Drifts Investigation of Possible Reaction Mechanisms for the Water-Gas Shift Reaction on High-Activity Pt- and Au-Based Catalysts. *J. Catal.* **2007**, *252*, 18-22.
3. Graf, P. O.; de Vlieger, D. J. M.; Mojet, B. L.; Lefferts, L. New Insights in Reactivity of Hydroxyl Groups in Water Gas Shift Reaction on Pt/ZrO₂. *J. Catal.* **2009**, *262*, 181-187.
4. Rodriguez, J. A. Gold-based Catalysts for The Water–Gas Shift Reaction: Active Sites and Reaction Mechanism. *Catal. Today* **2011**, *160*, 3-10.
5. Kalamaras, C. M.; Dionysiou, D. D.; Efstathiou, A. M. Mechanistic Studies of the Water-Gas Shift Reaction over Pt/Ce_xZr_{1-x}O₂ Catalysts: The Effect of Pt Particle Size and Zr Dopant. *ACS Catal.* **2012**, *2*, 2729-2742.
6. Yao, S. Y.; Xu, W. Q.; Johnston-Peck, A. C.; Zhao, F. Z.; Liu, Z. Y.; Luo, S.; Senanayake, S. D.; Martínez-Arias, A.; Liu, W. J.; Rodriguez, J. A. Morphological Effects of the Nanostructured Ceria Support on the Activity and Stability of CuO/CeO₂ Catalysts for the Water-Gas Shift Reaction. *Phys. Chem. Chem. Phys.* **2014**, *16*, 17183-17195.
7. Zhu, M.; Wachs, I. E. Iron-Based Catalysts for the High-Temperature Water–Gas Shift (HT-WGS) Reaction: A Review. *ACS Catal.* **2016**, *6*, 722-732.
8. Burch, R. Gold Catalysts for Pure Hydrogen Production in the Water-Gas Shift. *Phys. Chem. Chem. Phys.* **2006**, *47*, 5483-5500.
9. Rodriguez, J.A.; Liu, P.; Hrbek, J.; Evans, J.; Pérez, M. Water Gas Shift Reaction on Cu and Au Nanoparticles Supported on CeO₂(111) and ZnO(0001): Intrinsic Activity and Importance of Support Interactions. *Angew. Chem. Int. Ed.* **2007**, *46*, 1329-1332.

10. Vignatti, C.; Avila, M. S.; Apesteguía, C. R.; Garetto, T. F. Catalytic and Drifts Study of the WGS Reaction on Pt-Based Catalysts. *Int. J. Hydrogen Energy* **2010**, *35*, 7302-7312.
11. Barrio, L.; Kubacka, A.; Zhou, G.; E., Michael; Martínez-Arias, A.; Hanson, J. C.; Fernández-García, M.; Rodriguez, J. A., Unusual Physical and Chemical Properties of Ni in $\text{Ce}_{1-x}\text{Ni}_x\text{O}_{2-y}$ Oxides: Structural Characterization and Catalytic Activity for the Water Gas Shift Reaction. *J. Phys. Chem. C* **2010**, *114*, 12689-12697.
12. Xu, W. Q.; Si, R.; Senanayake, S. D.; Llorca, J.; Idriss, H.; Stacchiola, D.; Hanson, J. C.; Rodriguez, J. A. *In Situ* Studies of CeO_2 -Supported Pt, Ru, and Pt–Ru Alloy Catalysts for the Water–Gas Shift Reaction: Active Phases and Reaction. *J. Catal.* **2012**, *291*, 117-126.
13. Barrio, L.; Zhou, G.; González, I. D.; Estrella, M.; Hanson, J.; Rodriguez, J. A.; Navarro, R. M.; Fierro, J. L. G. *In Situ* Characterization of Pt Catalysts Supported on Ceria Modified TiO_2 for the WGS Reaction: Influence of Ceria Loading. *Phys. Chem. Chem. Phys.* **2012**, *14*, 2192-2202.
14. Zhao, F.; Liu, Z.; Xu, W.; Yao, S.; Kubacka, A.; Johnston-Peck, A. C.; Senanayake, S. D.; Zhang, A.-Q.; Stach, E. A.; Fernández-García, M. et al. A. Water-Gas Shift Reaction on Ni–W–Ce Catalysts: Catalytic Activity and Structural Characterization. *J. Phys. Chem. C* **2014**, *118*, 2528-2538.
15. Ashok, J.; Ang, M. L.; Terence, P. Z. L.; Kawi, S. Promotion of the Water-Gas-Shift Reaction by Nickel Hydroxyl Species in Partially Reduced Nickel-Containing Phyllosilicate Catalysts. *Chem. Cat. Chem.* **2016**, *8*, 1308-1318.
16. Sener, C.; Wesley, T. S.; Alba-Rubio, A. C.; Kumbhalkar, M. D.; Hakim, S. H.; Ribeiro, F. H.; Miller, J. T.; Dumesic, J. A. PtMo Bimetallic Catalysts Synthesized by Controlled Surface Reactions for Water Gas Shift. *ACS Catal.* **2016**, *6*, 1334-1344.
17. S. Tsunekawa; K. Ishikawa; Z. Q. Li; Y. Kawazoe and A. Kasuya. Origin of Anomalous Lattice Expansion in Oxide Nanoparticles. *Phys. Rev. Lett.*, **2000**, *85*, 3440.

18. M. D. Hernandez-Alonso; A. B. Hungria; A. Martinez-Arias; J. M. Coronado; J. C. Conesa; J. Soria and M. Fernandez-Garcia. Confinement effects in quasi-stoichiometric CeO₂ nanoparticles. *Phys. Chem. Chem. Phys.*, **2004**, 6, 3524.
19. Luo, S.; Nguyen-Phan, T. D.; Johnston-Peck, A. C.; Barrio, L.; Sallis, S.; Arena, D. A.; Kundu, S.; Xu, W. Q.; Piper, L. F. J.; Stach, E. A., et al. Hierarchical Heterogeneity at the CeO_x-TiO₂ Interface: Electronic and Geometric Structural Influence on the Photocatalytic Activity of Oxide on Oxide Nanostructures. *J. Phys. Chem. C* **2015**, 119, 2669-2679.
20. Toby, B. H., Von Dreele, R. B. GSAS-II: The Genesis of a Modern Open-Source All Purpose Crystallography Software Package. *J. Appl. Crystallogr.* **2013**, 46, 544-549.
21. Marinkovic, N. S.; Wang, Q.; Frenkel, A. I. *In Situ* Diffuse Reflectance IR Spectroscopy and X-ray Absorption Spectroscopy for Fast Catalytic Processes. *J. Synchrotron Rad.* **2011**, 18, 447-455.
22. Watanabe, S.; Ma, X.; Song, C. Characterization of Structural and Surface Properties of Nanocrystalline TiO₂-CeO₂ Mixed Oxides by XRD, XPS, TPR, and TPD. *J. Phys. Chem. C* **2009**, 113, 14249-14257.
23. Larsson, P. O.; Andersson, A. Complete Oxidation of CO, Ethanol, and Ethyl Acetate over Copper Oxide Supported on Titania and Ceria Modified Titania. *J. Catal.* **1998**, 179, 72-81.
24. Pojanavaraphan, C.; Luengnaruemitchai, A.; Gulari, E. Effect of Catalyst Preparation on Au/Ce_{1-x}Zr_xO₂ and Au-Cu/Ce_{1-x}Zr_xO₂ for Steam Reforming of Methanol. *Int. J. Hydrogen Energy* **2013**, 38, 1348-1362.
25. Fernández-Garcia, M.; Wang, X. Q.; Belver, C.; Iglesias-Juez, A.; Hanson, J. C.; Rodriguez, J. A. Ca Doping of Nanosize Ce-Zr and Ce-Tb Solid Solutions: Structural and Electronic Effects. *Chem. Mater.* **2005**, 17, 4181-4193.
26. Rodriguez, J. A.; Hanson, J. C.; Kim, J.-Y.; Liu, G.; Iglesias-Juez, A.; Fernández-García, M. Properties of CeO₂ and Ce_{1-x}Zr_xO₂ Nanoparticles: X-ray Absorption Near-Edge Spectroscopy,

- Density Functional, and Time-Resolved X-ray Diffraction Studies. *J. Phys. Chem. B.* **2003**, *107*, 3535-3543.
27. Wang, X.; Hanson, J. C.; Rodriguez, J. A.; Belver, C.; Fernández-García, M. The Structural and Electronic Properties of Nanostructured $\text{Ce}_{1-x-y}\text{Zr}_x\text{Tb}_y\text{O}_2$ Ternary Oxides: Unusual Concentration of Tb^{3+} and Metal $\leftrightarrow$ Oxygen $\leftrightarrow$ Metal Interactions. *J. Chem. Phys.* **2005**, *122*, 154711.
 28. Giordano, F.; Trovarelli, A.; de Leitenburg, C.; Giona, M. A Model for the Temperature-Programmed Reduction of Low and High Surface Area Ceria. *J. Catal.* **2000**, *193*, 273-282.
 29. Badri, A.; Binet, C.; Lavalley, J. C. An FTIR Study of Surface Ceria Hydroxyl Groups during a Redox Process with H_2 . *J. Chem. Soc., Faraday Trans.* **1996**, *92*, 4669-4673.
 30. Meunier, F. C.; Tibiletti, D.; Goguet, A.; Reid, D.; Burch, R. On the Reactivity of Carbonate Species on a Pt/CeO₂ Catalyst under Various Reaction Atmospheres: Application of the Isotopic Exchange Technique. *Appl. Catal. A Gen.* **2005**, *289*, 104-112.
 31. Soykal, I. I.; Sohn, H.; Ozkan, U. S. Effect of Support Particle Size in Steam Reforming of Ethanol over Co/CeO₂ Catalysts. *ACS Catal.* **2012**, *2*, 2335-2348.
 32. Holmgren, A.; Andersson, B.; Duprez, D. Interactions of CO with Pt/Ceria Catalysts. *Appl. Catal. B: Environ.* **1999**, *22*, 215-230.
 33. Wu, Z.; Li, M.; Overbury, S. H. On the Structure Dependence of CO Oxidation over CeO₂ Nanocrystals with Well-Defined Surface Planes. *J. Catal.* **2012**, *285*, 61-73.
 34. Hočevar, S.; Krašovec, U. O.; Orel, B.; Aricó, A. S.; Kim, H. CWO of Phenol on Two Differently Prepared CuO–CeO₂ Catalysts. *Appl. Catal., B* **2000**, *28*, 113-125.
 35. Liu, Y.; Hayakama, T.; Suzuki, K.; Hamakawa, S., Production of Hydrogen by Steam Reforming of Methanol over Cu/CeO₂ Catalysts Derived from $\text{Ce}_{1-x}\text{Cu}_x\text{O}_{2-x}$ Precursors. *Catal. Commun.* **2001**, *2*, 195-200.

36. Burch, R.; Goguet, A.; Meunier, F. C. A Critical Analysis of the Experimental Evidence for and against a Formate Mechanism for High Activity Water-Gas Shift Catalysts. *Appl. Catal., A* **2011**, *409-410*, 3-12.
37. Shinde, V. M.; Madras, G. Low Temperature CO Oxidation and Water Gas Shift Reaction over Pt/Pd Substituted in Fe/TiO₂ Catalysts. *Int. J. Hydrogen Energy* **2012**, *37*, 18798-18814.

TOC Graphic