BNL-114157-2017-JA

**In situ Tracking Kinetic Pathways of Li⁺/Na⁺ Substitution
During Ion-exchange Synthesis of Li_xNa_{1.5-x}VOPO₄F_{0.5}**

F. Wang

Submitted to Advanced Materials

August 2017

Sustainable Energy Technologies Department

Brookhaven National Laboratory

**U.S. Department of Energy
USDOE Office of Energy Efficiency and Renewable Energy (EERE),
Vehicle Technologies Office (EE-3V)**

Notice: This manuscript has been authored by employees of Brookhaven Science Associates, LLC under Contract No. DE- SC0012704 with the U.S. Department of Energy. The publisher by accepting the manuscript for publication acknowledges that the United States Government retains a non-exclusive, paid-up, irrevocable, world-wide license to publish or reproduce the published form of this manuscript, or allow others to do so, for United States Government purposes.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or any third party's use or the results of such use of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

In situ Tracking Kinetic Pathways of Li⁺/Na⁺ Substitution during Ion-exchange Synthesis of Li_xNa_{1.5-x}VOPO₄F_{0.5}

Young-Uk Park,^{1, 2} Jianming Bai,³ Liping Wang,¹ Gabin Yoon,^{2, 5} Wei Zhang,¹ Hyungsub Kim,² Seongsu Lee,⁴ Sung-Wook Kim,^{1, 4} J. Patrick Looney,¹ Kisuk Kang^{2, 5,*} and Feng Wang^{1,*}

¹*Sustainable Energy Technologies Department, Brookhaven National Laboratory, Upton, NY 11973, USA*

²*Department of Materials Science and Engineering, Research Institute of Advanced Materials (RIAM), Seoul National University, Seoul 151-742, Republic of Korea*

³*National Synchrotron Light Source II, Brookhaven National Laboratory, Upton, NY 11973, USA*

⁴*Korea Atomic Energy Research Institute, P.O. Box 105, Daejeon 305-600, Republic of Korea*

⁵*Center for Nanoparticle Research, Institute for Basic Science, Seoul National University, Seoul 151-742, Republic of Korea*

KEYWORDS. Ion-exchange, Li-ion Batteries, Quasi-equilibrium structure, *In situ* X-ray Diffraction, First Principles

ABSTRACT: Ion exchange is a ubiquitous phenomenon central to wide industrial applications, ranging from traditional (bio)chemical separation to the emerging *chimie douce* synthesis of materials for batteries and other energy applications. The exchange process is complex, involving substitution and transport of different ions under *non-equilibrium* conditions, and thus difficult to probe, leaving a gap in mechanistic understanding of kinetic exchange pathways toward final products. Herein, we report *in situ* tracking kinetic pathways of Li⁺/Na⁺ substitution during solvothermal ion-exchange synthesis of Li_xNa_{1.5-x}VOPO₄F_{0.5} ($0 \leq x \leq 1.5$), a promising multi-Li polyanionic cathode for batteries. The *real-time* observation, corroborated by *first-principles* calculations, reveals a selective replacement of Na⁺ by Li⁺, leading to peculiar Na⁺/Li⁺/vacancy orderings in the intermediates. Contradicting the traditional belief of facile topotactic substitution *via* solid solution reaction, an abrupt two-phase transformation occurs and predominantly governs the kinetics of ion exchange and transport in the 1D polyanionic framework, consequently leading to significant difference of Li stoichiometry and electrochemical properties in the exchanged products. The findings may help to pave the way for rational design of ion exchange synthesis for making new materials.

INTRODUCTION

Ion exchange is a ubiquitous phenomenon occurring naturally in various types of materials such as clays, zeolites, resins, hydrous oxides, phosphates, and fast ion conductors. It has been extensively studied for more than a century because of its wide application in industry for chemical/biochemical separation and purification.^{1,2} The ion-exchange reaction has now been widely applied as a soft chemistry (*chimie douce*) approach for preparing new quasi-equilibrium, uniquely structured phases that are otherwise unobtainable using direct chemical reactions. The ion-exchange reaction is normally performed in molten salt or solvothermal conditions. Heating to high temperature (*e.g.*, 300 °C or above) is needed in the former case, often leading to decomposition of the material or the formation of a more stable structure. Using ion exchange reactions under mild solvothermal conditions (below 200 °C) would be preferable in many cases wherein the reaction is performed at the lowest possible temperature that is sufficient to accelerate exchange kinetics.

Ion exchange has recently been used as an alternative route for preparation of novel electrode materials with quasi-equilibrium structures for Li-ion batteries (LIBs).³⁻¹⁸ Notably,

many battery materials for LIBs have been synthesized from existing Na compounds *via* Li⁺/Na⁺ ion-exchange reaction. This research area was initiated by Delmas *et al.* in preparing the metastable O2-LiCoO₂ phase from P2-Na_{0.70}CoO₂,⁷ followed by the preparation of layered LiMnO₂,^{3,4} Na_{2/3}[M_xMn_{1-x}]O₂ ($M = \text{Co, Ni, Fe, Li, or Mg}$),^{17,18} and Li(Na)Ni_{0.5}Mn_{0.5}O₂.¹⁹ Those early research activities on layered oxides were followed by the discovery of diverse polyanionic compounds through ion exchange, which began with rhombohedral Li₃V₂(PO₄)₃ and orthorhombic Li₂FePO₄F by Nazar *et al.*,^{10,11} inspired by the work on the rhombohedral form of Li₃Fe₂(PO₄)₃.^{8,9} Recently, many novel compounds have been invented through Li⁺/Na⁺ ion exchange, including the carbonophosphates Li₃FePO₄CO₃ and Li_{2.67}Na_{0.63}MnPO₄CO₃ by Ceder and co-workers,^{5,6} and the (fluoro)phosphates Li₂MnPO₄F, Li_{1.1}Na_{0.4}VPO_{4.8}F_{0.7}, and Li₃NaFe₃(PO₄)₂(P₂O₇) and alluaudite Li_{0.67}MPO₄ ($M = \text{Fe or Mn}$) by Kang and co-workers.¹²⁻¹⁶ Although the electrochemical performance of some of these new materials is impressive, potentially paving the way toward the discovery of new electrode materials, their practical use in batteries has nevertheless been challenging for various reasons. The issues include (i) insufficient Li content in

the exchanged products, (ii) phase separation and decomposition during the reaction, and (iii) poor electrochemical properties, largely arising from high structural disordering of the exchanged phases. Optimization of the experimental conditions has largely been performed on a *trial-and-error* basis, necessitating developing general guidelines for the synthesis of new compounds *via* the ion-exchange reaction; and certainly an elaborate study on the ion-exchange mechanism is vital to achieving this goal.

For the specific application to LIBs, very few mechanistic studies of ion-exchange reactions can be found in the literature and most of these investigations focused on layered oxides and were performed *ex situ*.^{18–21} Dahn and coworkers investigated the ion-exchange process from P2-Na_{2/3}[Ni_{1/3}Mn_{2/3}]O₂ to T2-Li_{2/3}[Ni_{1/3}Mn_{2/3}]O₂ at controlled Li/Na ratios and discovered an intermediate phase of Li_{1/3}Na_{1/3}[Ni_{1/3}Mn_{2/3}]O₂ with alternating alkali-metal layers of Li and Na.¹⁸ Delmas *et al.* conducted thorough studies of ion exchange in P2-Na_{0.7}CoO₂ using a combination of X-ray diffraction (XRD) measurements and theoretical calculations,²⁰ disclosing a biphasic reaction process during which a new intermediate Na phase of P2*-Na_{0.5}CoO₂ was formed and subsequently transformed into O2-LiCoO₂. Very recently, the ion-exchange mechanism of layered LiNi_{0.5}Mn_{0.5}O₂ was investigated using XRD measurements, revealing several sequential phase transformations with different kinetics.²¹ However, findings for ion-exchange reactions in layered oxides are not generally applicable to other types of compounds such as polyanionic compounds, an important class of high-energy multi-Li cathodes that have significantly different crystal structures. Alkali ion exchange and transport in polyanionic compounds would be expected to be different from those in layered oxides. Moreover, due to different kinetics among intermediate phases, precise determination of the mechanism(s) for each phase would be challenging using *ex situ* analysis of the ion-exchange reaction. As exchange processes are complex, involving liquid-mediated ion substitution and transport in solids under *non-equilibrium* conditions, it is difficult to probe, and to date *in situ* studies of ion-exchange reactions is largely lacking in literature.

In this work, an *in situ* reactor was developed for monitoring the Li⁺/Na⁺ ion-exchange reaction under solvothermal conditions using *time-resolved* synchrotron XRD techniques and applied to a polyanionic compound, Na_{1.5}VOPO₄F_{0.5}, which is known to be Li⁺/Na⁺ ion-exchangeable.^{16,22} The compound and its derivatives have been frequently reported as high-performance cathode materials for Li- and Na-ion batteries.^{16,23–33} Complementary neutron diffraction studies were also performed to identify the Li sites in the exchanged phases by taking advantage of the high scattering cross-section of the Li nucleus (in contrast to the negligible X-ray scattering of Li or Na ions, with only two or three electrons). Real-time measurements provide details about the structural transformation and reaction kinetics at different stages, and in combination with neutron measurements and *ab initio* calculations, this study reveals a peculiar Li/Na/vacancy ordering and possible diffusion pathways, indicating a completely different exchange process than that of layered oxides. A thorough investigation was conducted on the effects of key experimental parameters (temperature, Li/Na ratio, Li concentration) on the extent of reaction (*i.e.*, the final Li content, *x*) and phase-transformation dynamics. The findings provide guidance to optimizing the synthesis for obtaining exchanged products, of maximized Li-content and excellent electrochemical performance for use as cathode materials in LIBs. We believe that this study could

pave the way for the rational design of ion-exchange synthesis of materials for batteries or other energy applications.

EXPERIMENTAL AND CALCULATIONS

Materials synthesis. Na_{1.5}VOPO₄F_{0.5} powders were prepared using the procedure from a previous report,^{16,27} where a two-step solid-state reaction was used. A series of Li_{*x*}Na_{1.5–*x*}VOPO₄F_{0.5} phases (*x* = 0.62, 1.02, and 1.34) was prepared *via ex situ* the Li⁺/Na⁺ ion-exchange reaction of Na_{1.5}VOPO₄F_{0.5}. A LiBr solution (solvent: 1-hexanol) was mixed with the Na_{1.5}VOPO₄F_{0.5} powder in an autoclave reactor. Then, the reactor was placed in an oven, and the ion-exchange reaction was performed at 160°C for 48 h. We systematically changed the molarity and volume of the LiBr solution to obtain a series of Li_{*x*}Na_{1.5–*x*}VOPO₄F_{0.5} phases with various Li contents (*x*). The atomic ratios of Li to Na in the powder samples were determined using inductively coupled plasma (ICP) spectroscopy (Polyscan 60E, Thermo Jarrell Ash).

***In situ* synchrotron XRD measurements for studying ion-exchange reaction.** A glass capillary was used as an *in situ* reactor for probing Li⁺/Na⁺ ion-exchange reaction in Na_{1.5}VOPO₄F_{0.5}. The capillary reactor was located in the path of an X-ray beam to track the ion-exchange process in real time. To obtain a stronger diffraction signal, Na_{1.5}VOPO₄F_{0.5} powder was placed at the bottom of the capillary through which most of the X-ray beam passes (*i.e.*, the X-ray zone). A solution made of LiBr salt and 1-hexanol solvent was added to the capillary, and the reactor was sealed with an alumina rod and glue. The reactor was uniformly heated using a heating coil, and the temperature was monitored using a K-type thermocouple. Temperature calibration was performed by placing another thermocouple in the X-ray zone and obtaining a linear relationship between different temperatures from the two thermocouples. The capillary was continuously rotated during the XRD measurements to prevent preferred orientation of the powder and to ensure homogenous reaction. *In situ* synchrotron XRD measurements were conducted at the X14A beamline of the National Synchrotron Light Source (NSLS) at Brookhaven National Laboratory. The X-ray wavelength was ~0.779 Å. Each XRD scan took approximately 6 minutes with a 2θ range from 4° to 50°. Temperature-controlled XRD measurements for the *ex situ* powders were performed using the same experimental setup.

Neutron diffraction. Neutron diffraction (ND) data were collected over the 2θ range from 0° to 180° with a step size of 0.05°, and a wavelength of 1.83429 Å was supplied by a Ge(331) single-crystal monochromator on a high-resolution powder diffractometer (HRPD) at the Hanaro facility of the Korea Atomic Energy Research Institute. Rietveld refinements of the ND and XRD data were performed using Fullprof software.³⁷

Transmission electron microscopy (TEM). TEM images and electron diffraction patterns were obtained from pristine and exchanged Li_{*x*}Na_{1.5–*x*}VOPO₄F_{0.5} powders using a JEOL-2100F equipped with a Schottky field-emitter, operated at an accelerating voltage of 200 kV.

Electrochemical tests. Before the tests, the Li_{*x*}Na_{1.5–*x*}VOPO₄F_{0.5} powders (*x* = 1.02 and 1.34) were ball-milled with carbon black (20 wt%) for 6 h. A slurry of 90 wt% ball-milled mixture and 10 wt% polyvinylidene fluoride (Sigma-Aldrich) dispersed in *N*-methyl-2-pyrrolidone (Sigma-Aldrich) was prepared and cast on Al foil. The loading of the active material on the electrode was approximately 2–3 mg cm^{–2}, and the net

active content was 72 wt%. Electrochemical cells were assembled into CR2032-type coin cells with a Li metal counter electrode, separator (Celgard 2400, Celgard), and electrolyte (1 M LiPF_6 in a mixture of ethyl carbonate/dimethyl carbonate, 1:1 v/v) in an Ar-filled glove box. All the tests were performed at room temperature using a potentiostat/galvanostat (BT2000, Arbin or WBCS 3000, WonA Tech) with a voltage window of 2.5–4.5 V or 2.0–4.5 V (vs. Li^+/Li). 1C means 141 and 145 mA g^{-1} for the $x = 1.02$ and 1.34 electrodes, respectively.

Computational details. All the calculations were performed on a density functional theory (DFT) platform using the spin-polarized generalized gradient approximation (GGA)³⁸ with Perdew–Burke–Ernzerhof (PBE) parameterization. In addition, the GGA+ U method^{39,40} was adopted to correct the incomplete description of self-interaction in transition metal oxide systems. Values of 5.0 and 1.0 eV were adopted for the on-site Coulomb term U and exchange term $\tilde{J}$ of V ions, respectively.²⁶ We used projector-augmented wave (PAW) pseudopotentials^{41,42} as implemented in the Vienna *ab initio* simulation package (VASP).⁴³ All the geometric relaxations were performed until all the forces in the system converged within 0.008 eV/Å under a kinetic energy cutoff of 500 eV. To study the phase reaction during ion exchange of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ system ($0 \leq x \leq 1.5$), we generated all possible Li–Na–vacancy orderings within the unit cell using the CASM program. We note that the vacancies on the Li/Na site can be formed in the intermediate during ion-exchange. However, since the ICP data of $\text{Li}_{0.62}\text{Na}_{0.88}\text{VOPO}_4\text{F}_{0.5}$ phase and the electrochemical profile $\text{Li}_{1.34}\text{Na}_{0.16}\text{VOPO}_4\text{F}_{0.5}$ indicated the low possibility of the change in the oxidation state of V along with the possible vacancies on the Li/Na site, in this calculation we assumed that the vacancies would not be formed on the Li/Na site during the ion-exchange.⁴⁴ Then, each configuration was relaxed using the GGA+ U method. The activation energy of Na diffusion in $\text{Li}_{1.0}\text{Na}_{0.5}\text{VOPO}_4\text{F}_{0.5}$ was calculated using the NEB method.⁴⁵ Na ions were allowed to move in the $\text{Li}_{15/16}\text{Na}_{0.5}\text{VOPO}_4\text{F}_{0.5}$ unit cell. Seven linearly interpolated images between the initial and final states were generated to describe the diffusion pathways of Na ions. During the nudged elastic band (NEB) calculation, the lattice parameters were fixed, whereas the internal structures were allowed to relax.

RESULTS AND DISCUSSION

Exchange-driven Two-phase Transformation in $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$

A series of synchrotron XRD measurements were performed on the products from the Li^+/Na^+ exchange of $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ in LiBr solution under different experimental conditions, such as the LiBr concentration, ratio of the initial amount of Li in solution to that of Na in $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ (*i.e.*, the Li/Na ratio), and reaction time. The main results were presented in Supplementary Figure S1. When sufficient reaction time was allowed, the Li content (x) of the exchanged products ($\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$) increased linearly with the LiBr concentration, as determined by ICP spectroscopy (Figure S1a), but was not affected by the Li/Na ratio (Figure S1b). Interestingly, in contradiction to the traditional belief that Li substitution into isostructural Na compounds occurs *via* continuous displacement, ion exchange in $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ appears to involve an unexpected two-phase transformation as suggested by the presence of a second Li-rich phase in the intermediates ($Pnmm$, No. 58; as to be discussed below), in addition to the original one ($P4_2/mnm$, No. 136; Figure S1c).

To identify how the phase transformation proceeded and was coupled to other processes (*i.e.*, solid-solution reaction, as expected) during the Li^+/Na^+ exchange process in $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$, a series of *in situ* synchrotron XRD measurements were performed using a specially designed reactor shown in Figure 1a (see the details of the experimental setup and measurements in the Methods section). The *in situ* investigation was first performed to determine the effect of the molarity of the LiBr solution on the exchange process at a fixed temperature (160°C), with the reactor being rapidly heated to the desired temperature (within approximately 5 min) and maintained at that temperature throughout the entire exchange process. The obtained time-resolved XRD patterns for different LiBr concentrations (0.5, 1, 2, 3, 4, and 5 M) were presented in Figure 1b and Supplementary Figure S2a–f, where an enlarged view of the patterns containing (111), (002), and (222) diffraction peaks was displayed to show subtle structural changes. Except for the lowest LiBr molarity (0.2 M), a two-phase reaction followed by a solid-solution reaction occurred during the ion exchange regardless of the molarity. Strong peaks associated with a Li-rich phase were detected after approximately 10 min, as observed in the third XRD pattern, in addition to the peaks associated with the Na-rich phase (Figure 1b), indicating that the two-phase reaction proceeds simultaneously during heating. From the XRD data (as presented in Figure 1b and Figure S2), time dependent phase transformation for different LiBr concentrations were obtained (Figure 1d; illustrated by the evolution of the peak position of (002)), showing the different stages of the ion-exchange, namely, two-phase, solid-solution, and no-change.

For the low LiBr concentration (0.2 M), the final product ($x \approx 0.3$) was isostructural to the pristine phase ($x = 0$), where x in $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ was estimated based on Vegard’s law³⁴ (Supplementary Figure S3). Between the two end members ($x = 0$ and ~ 0.3), only solid-solution reaction was detected, indicating that the Li solubility in the $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ framework ($P4_2/mnm$) is approximately 0.3 at 160°C (Supplementary Figure S2a). For the higher LiBr concentrations (0.5–5 M), two-phase reactions occurred from the very beginning and lasted for approximately 1 h, independent of the LiBr concentration. Interestingly, the Na-rich phase was not pure $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ ($x = 0$) but already contained a significant amount of Li ($x \sim 0.3$), as measured from the second XRD pattern. This finding was common for all the LiBr concentrations (0.5–5 M; marked by asterisks in Figure S2g), indicating a sudden transformation of the pristine Na phase into an exchanged phase with substantial Li content, with the original framework ($P4_2/mnm$) maintained. Because each XRD scan took approximately 5 min, the Li^+/Na^+ ion-exchange reaction up to $x \approx 0.4$ was complete within 10 min, which explains the nearly undetectable solid-solution region ($0 < x < \sim 0.4$) for higher molarities (0.5–5 M). This fast ion exchange implies facile interdiffusion of Na^+ and Li^+ ions in the tetrahedral framework of $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$. The composition ranges of the Na-rich and Li-rich phases in the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ system vary, with the latter being significantly expanded when the LiBr concentration increases to provide more sources of Li, as indicated in the histogram (Li content x vs. LiBr concentration) in Figure S2g. Notably, a gap between the Na-rich and Li-rich phases exists at $x \sim 0.4$ – 0.5 (shaded region), independent of the LiBr concentration, which suggests an abrupt change in crystal structures near this composition. Below this Li content, only a solid solution is present with limited Li being accommodated (up to approximately 0.4), with the original tetrahedral struc-

ture with a space group of $P4_2/mnm$ being maintained^{16,27,35}. At $x = 0.5$ and above, nucleation and growth of the new Li-rich phase ($Pnmm$; No. 58) became involved, and the kinetics of Li^+/Na^+ exchange were not solely determined by ion interdiffusion in a single solid phase, but also through liquid/solid and solid/solid interfaces. This difference may explain the observation of the miscibility gap in Figure S2g (which was also observed during ion exchange at different temperatures, as shown in Figure 4b; see the discussion below).

First-principles calculations were performed to investigate the composition-dependent phase behavior for different Li concentrations (see details in Methods). As demonstrated by the formation energy plot of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ system ($0 \leq x \leq 1.5$) in Figure 1e, there are many Li–Na mixed phases with configurations that are energetically more stable (negative energy points) than the initial Na or end-member of the Li phases regardless of the compositions. Considering the lowest energy points at each composition and the elevated temperature of the ion-exchange process, the intermediates of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ can have a wide range of Li/Na ratios (or x values). This finding provides theoretical support for the *in situ* observations, with clear indications of a wide range of Na-rich and Li-rich solid-solution phases in the exchanged intermediates.

In the precursor $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ (space group of $P4_2/mnm$), VO_5F octahedra and PO_4 tetrahedra are repeatedly linked along the a and b directions by corner sharing, forming a 3D open framework.^{16,27,35} The subtle structural change in the exchanged intermediates, $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$, was determined by high-resolution synchrotron XRD combined with Rietveld refinements. The results from three representative samples were provided in Figure 2a for $x = 0.62$ (low end-member of Li-rich phase) and Supplementary Figure S4 (for high-Li-content samples: $x = 1.02$ and 1.34). The crystallographic data were summarized in Supplementary Tables S1–S6. In attempts to analyze the XRD data of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phases ($x = 0.62, 1.02$, and 1.34), assuming they all adopt the same space group as the pristine phase, $x = 0$ ($P4_2/mnm$; No. 136), many reflections could not be indexed. However, the reflections could be well indexed using $Pnmm$ (No. 58), a subgroup of $P4_2/mnm$ with broken a – b symmetry, as demonstrated in Figure 2b. No splitting was detected in the reflections with $h = k$, which essentially remained the same as those in the pristine sample ($x = 0$); however, strong peak splitting was observed for those with $h \neq k$. This finding can be explained by the reduced symmetry with the space group change from $P4_2/mnm$ (tetragonal, $a = b \neq c$) to $Pnmm$ (orthorhombic, $a \neq b \neq c$). The new $Pnmm$ framework for $x = 0.62$ was slightly distorted compared with the $P4_2/mnm$ one for $x = 0$ (inset of Figure 2b) because of selective replacement of Na^+ by Li^+ ions (with a smaller radius, as discussed below). Therefore, instead of ion substitution *via* a solid-solution reaction as traditionally believed, two-phase transformation clearly occurred (Figure 1b–d) because of the selective replacement of Na^+ by Li^+ ions. The clear gap in the calculated cell volume between the Na-rich and Li-rich phases in the two-phase region (Supplementary Figure S5) suggests that the crystal structure of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ changed phase from $P4_2/mnm$ to $Pnmm$ at approximately $x = 0.5$.

Kinetic Limitation to Li^+/Na^+ Ion Exchange

As a complementary approach to the bulk XRD structural analysis, local structural examination of individual particles using transmission electron microscopy (TEM) was also performed. Figure 2c presents a typical TEM image and electron

diffraction pattern from a single $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ particle (oriented along the (001) direction). The material is micron-sized and generally consisted of phase-pure single-crystalline particles, which were inherited by the exchanged products (see TEM images in Supplementary Figure S6), indicating a topotactic ion-exchange process without particle pulverization. Regardless of the LiBr concentration, the Na-rich phase did not completely disappear for a few hours, in contrast to the rapid formation of Li-rich phase (in a few minutes) (Figure 1b–c and Figure S2). This finding suggests the dominance of sluggish phase propagation across the micron-sized particles over the ion-exchange process, which may be well described by a core–shell model, namely rapid formation of Li-rich phases at the shell and Na-rich ones at the core, as illustrated in Figure 2d. Other models, such as domino-cascade model and particle-by-particle model, as adopted in literatures to explain the two-phase phenomenon of LiFePO_4 , were also considered; however, the plausibility of using those models to explain our findings is low due to the large particle size and sluggish kinetics.^{46–48}

As demonstrated in the *in situ* XRD patterns (Figure 1b–c and Figure S2), the diffraction peaks of the Li-rich phases continuously shifted toward higher angles even in the two-phase region, indicating that the ion-exchange experiments were run under *non-equilibrium* conditions.[‡] In other words, while the Na-rich phases in the core part were gradually consumed, the Li-rich phase in the rest of the particle underwent further ion-exchange reaction (Figure 2d). After the Na-rich phase completely disappeared, the Li-rich phases ($x > 0.5$; $Pnmm$) continued to gain Li^+ ions from the LiBr solution. This continuous increase in Li content of the Li-rich phase throughout the ion-exchange reaction creates another solid-solution region that lasts for a long period (shown in the red region of Figure 1b) at a rate two orders slower than that of the solid-solution reaction in the Na-rich one (which is complete in minutes). This finding implies slow Na diffusion in the $Pnmm$ framework. Previous studies on ion-exchange reactions in mixed oxides noted that when larger ions were replaced by smaller ones, the framework would shrink, leading to reduced ionic conductivity.[‡] Nonetheless, this explanation may not fully explain our *in situ* observation because the lattice shrinkage ($\Delta V = -1.1\%$; $0 \leq x \leq 0.4$) was negligibly small.

The two-phase transition is overlapped with the solid solution in the Li-rich phase throughout a fairly wide range of x (e.g., $0.63 < x < 1.07$ for 5 M; dashed circle in Figure 1b), wherein x of the Li-rich phase gradually increased until the Na-rich phase completely disappeared. Based on the proposed core–shell model (Figure 2d), x at the completion of the two-phase transformation likely depends on how fast the Na-rich phase (core) was consumed and how fast the Li-rich phase (shell) was further ion-exchanged during the consumption of the Na-rich core. Meanwhile, the Li contents of the Li-rich phases in the multi-phase regions for 3–5 M were scattered over a wide range for the first few scans (Supplementary Figure S7), implying large local fluctuations in the LiBr concentration in the solution at the beginning of the reaction. It is presumed that beyond 3 M, the limited room-temperature solubility of LiBr in 1-hexanol (Supplementary Figure S8) prevented the formation of a uniform LiBr solution free of precipitation until sufficient temperature and time were allowed.

With the excess amount of Li sources (Li/Na ratio of 4:1 for 1 M and 10:1 for 2–5 M), high Li contents of the final products (i.e., the maximum x values) were attained in the LiBr solution with high molarity (Figure S2g), indicating their

strong dependence on the chemical equilibrium. The ion-exchange reaction can be expressed as follows:

where R^- represents an ion-exchanger matrix (*i.e.*, the $[\text{VOPO}_4\text{F}_{0.5}]^{1.5-}$ framework for this case). The thermodynamic equilibrium constant for this reaction, K_T , is defined as

$$K_T = \frac{(a_{\text{Na}^+})(\bar{a}_{\text{Li}^+})}{(a_{\text{Li}^+})(\bar{a}_{\text{Na}^+})}, \quad (3)$$

where a_{Na^+} and a_{Li^+} are the activities of Na^+ and Li^+ ions, respectively, in an ion-exchange medium, which could be an aqueous or nonaqueous solvent, or molten salt bath (nonaqueous solvent for this case).¹ $\bar{a}_{\text{Na}^+}$ and $\bar{a}_{\text{Li}^+}$ are the activities of Na^+ and Li^+ ions in the $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ and $\text{Li}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ phases, respectively. The activities for the ions in the solvent can be readily determined from the molar concentration, whereas those in the exchanger phase cannot be readily determined. However, according to previous reports,¹ the activities are proportional to the mole fractions of the exchanging ions in the exchanger phase. For our case, $\bar{a}_{\text{Na}^+}$ and $\bar{a}_{\text{Li}^+}$ are proportional to X_{Na^+} (*i.e.*, $1.5-x$) and X_{Li^+} (*i.e.*, x) in $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$, respectively. a_{Na^+} can be considered a constant because we observed that the amount of NaBr in the solution already exceeded its solubility limit at the very beginning of the reaction (Supplementary Figure S9). Because Na^+ ions are effectively excluded from the reaction by the precipitation, the equilibrium position of this reaction is expected to further shift to the right based on *Le Chatelier's* principle.¹ By assuming that most NaBr exists as a solid (*i.e.*, $a_{\text{Na}^+} \approx 1$), we can make the following approximation:

$$K_T \approx \frac{x}{[\text{LiBr}](1.5-x)}. \quad (4)$$

Therefore, x should be proportional to the concentration of the LiBr solution to reach an equilibrium state at a given temperature (*see* green patterns in Figure 1b–c for dynamic equilibrium region). The delay in reaching the equilibrium state $[\text{LiBr}]$ may provide another explanation for the slower kinetics of the Li-rich solid solution region ($x > 0.5$; low X_{Na^+}) compared with the Na-rich one ($x < 0.4$; high X_{Na^+}).

Ionic Ordering in $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$

By taking advantage of the high sensitivity of neutron scattering to lithium, neutron powder diffraction (NPD) measurements were performed to determine the occupancies of Li^+ and Na^+ ions in the crystal structure of the exchanged phases along with Rietveld refinements (using the space group of $Pnmm$). The results for $\text{Li}_{0.62}\text{Na}_{0.88}\text{VOPO}_4\text{F}_{0.5}$ were presented in Figure 3a (*see* also Supplementary Tables S7–S9 for the refinement results). Based on the refinement results, the Li content (x) in the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phase was ~ 0.52 , which is smaller than the value of 0.62 determined by ICP but close to the predicted value of $x=0.5$ as the lowest energy state (Figure 1e). Considering that some residual Li salts may remain in the samples even after washing, slightly higher estimation of Li contents is presumed in the ICP results.

Most interestingly, the refinement results indicated that Na^+ ions were aligned along the a direction and that these 1D Na channels, Li channels, and empty channels were alternatively repeated, resulting in a peculiar Li/Na/vacancy ordering in the ab plane (Figure 3b–c). The empty channels (green arrows

in Figure 3b) can act as an effective pathway for Li/Na interdiffusion, leading to facile ion exchange. The presence of the 1D Na array was also confirmed by *first-principles* calculations for $x = 0.5$ (Supplementary Figure S10), thereby explaining why the $x = 0.5$ composition has the lowest formation energy (denoted as a circle in Figure 1e), far below the tie line between the pure Na phase ($x = 0$) and pure Li phase ($x = 1.5$) (*see* the Discussion section). The anisotropic distribution of Na^+ and Li^+ ions in the ab plane for the $x = 0.5$ composition should have caused the space group to change from $P4_2/mnm$ to $Pnmm$ (as observed in the *in situ* experiments) considering that the symmetry of the a and b directions is maintained in $P4_2/mnm$ but broken in $Pnmm$. The Li/Na configurations in the ab plane for $x = 0.5$, 1.0, and 1.5 predicted from the *first-principles* calculations were shown in Supplementary Figure S10, showing the similarity in the trend of the lattice parameter change as a function of the Li content x (*see* the comparison between the theory and measurements in Figure S10d).

The obtained spatial arrangement/ordering of ions in the ab plane for intermediates with high Li contents (*i.e.*, $\text{Li}_{1.02}\text{Na}_{0.48}\text{VOPO}_4\text{F}_{0.5}$, $\text{Li}_{1.34}\text{Na}_{0.16}\text{VOPO}_4\text{F}_{0.5}$) were illustrated in Figure 3d–e. The empty channels were detected even for the $x = 1.02$ phase, suggesting that they are accessible in most of the Li-rich solid-solution region ($x > 0.5$). In the pristine sample ($\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$) with $P4_2/mnm$ space group, the eight Na1-type sites were almost fully occupied, whereas the eight Na2-type sites were occupied only up to 50% (in one unit cell). As the bond length between the two nearest Na2 sites is too short (2.026 Å), only four out of eight Na2 sites can be occupied simultaneously. Because of the $P4_2/mnm$ symmetry, the probability of finding Na in these eight Na2 sites is the same; under this symmetry (without phase transformation), the Li^+/Na^+ exchange proceeds in two dimensions. With ion exchange, Li ions take one of the Na1 sites in the pristine crystal and reduce the tetragonal symmetry to orthorhombic ($P4_2/mnm$ to $Pnmm$), and the pristine eight Na1 sites split into four Na1 (mainly occupied by Na) and four Li1 sites (fully occupied by Li). The eight Na2 sites with 50% percentage occupancy in the pristine crystal are reduced to four Na2 sites with full occupancy. The Li ion exchange of Na ions first occurs along the a direction, namely 1D transport. Meanwhile, we observed an ordered repetition of three types of channels, Li, Na, and empty channels, which may be explained by two possible reasons. First, a Li^+ ion in the Li1 site has a tendency to move from the center position of the augmented triangular prism site (*i.e.*, original Na1 and Na2 sites in the pure Na phase) because this site is too spacious for a Li^+ ion, increasing the distance between Li1 and other sites. Second, by replacing more Na^+ ions with Li^+ ions, the Na^+-Na^+ repulsion becomes weaker, and therefore, the positions of Na^+ ions sensitively change.

The dynamic ion ordering evolution is directly correlated to the change in lattice parameters a and b (*i.e.*, $|a-b|$), which was illustrated in Figure 3f. The $|a-b|$ value increases from 0 to 0.0854 because of the asymmetry in the exchanged phases ($x=0.5$) and then decreases with further Li/Na replacement. The broken symmetry is due to the peculiar Na ordering (*i.e.*, the 1D Na array). Therefore, the degree of Na ordering in the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ framework varies with x or temperature and can be compared using the difference between lattice parameters a and b (*i.e.*, larger $|a-b|$ values for stronger orderings). The x and temperature dependence of the $|a-b|$ value was also confirmed by the *in situ* experiments (Supplementary Figure S11), with thermal expansion being considered, using the calibrated expansion coefficients of various $\text{Li}_x\text{Na}_{1.5-x}$

$x\text{VOPO}_4\text{F}_{0.5}$ phases ($x = 0, 0.62, 1.02, \text{ and } 1.34$) listed in Supplementary Table S10. The broken symmetry can also be partially recovered by heating to higher temperatures, which induces a phase transition to $I4/mmm$ with higher symmetry (free of Na ordering), as illustrated by the temperature-resolved XRD patterns in Figure S12. The transition between $Pnmm$ and $I4/mmm$ with characteristic peak splitting of (hkl) reflections ($h \neq k$) is reversible within limited temperature ranges for all ion-exchanged phases of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ ($x = 0.62, 1.02, \text{ and } 1.34$) (Supplementary Figure S12). Similarly, the symmetry change in $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ from $P4_2/mnm$ to $I4/mmm$ with the loss of Na ordering was also reported earlier, albeit at higher temperature (~ 500 K).³⁵ For all x , the $|a-b|$ value gradually decreased with increasing temperature and eventually reached zero ($I4/mmm$), indicating the loss of the ordering (also illustrated in Figure 3f).

Thermodynamic and Kinetic Aspects of Ion Exchange

The temperature dependence of ion exchange in $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ was also studied using *in situ* XRD measurements at fixed Li/Na ratio (10:1) and in 2 M LiBr solution (Figure 4a–b). During the measurements, the temperature was kept constant for a long period until the change in the XRD patterns was negligible. Similar to the observation at 160°C , an abrupt increase in Li content x was observed from 0 to ~ 0.3 at 80°C at the very beginning (circle in Figure 4b), suggesting the fast Li/Na interdiffusion kinetics in the $P4_2/mnm$ framework even at such low temperature. Nevertheless, the solid-solution reaction became detectable (in contrast to its absence at 160°C) and extended to temperatures as high as 120°C , where the maximum x value was ~ 0.5 (green triangles in Figure 4b), indicating the substantial Li solubility in the Na-rich phase ($P4_2/mnm$ framework). The Li-rich phase was first detected in the middle of the 80°C region, and the initial Li content ($x \approx 0.5$) gradually increased with time (purple circles in Figure 4b). The Li-rich solid-solution region ($x > 0.5$) overlapped with the Na-rich one ($x < 0.5$) for more than 10 h, resulting in a two-phase region between the Na-rich and Li-rich phases ($P4_2/mnm$ vs. $Pnmm$), ranging from 80°C to 120°C (Figure 4b). Thus, even in the two-phase region, the composition of the Na-rich and Li-rich phases changed over a wide range ($0.3 < x < 0.5$ and $0.5 < x < 0.9$, respectively), which was similar to the findings of the concentration-controlled experiments (Figure 1b–e). This two-phase reaction slowed down with time in each temperature region but hardly reached equilibrium (see Supplementary Figure S13). Therefore, the completion of the two-phase transformation required both sufficient reaction time and temperature, reminiscent of a thermally activated process.

Interestingly, the Li content (x) increased with temperature both in the Na-rich and Li-rich solid-solution regions (Figure 4b). The temperature dependence of x can be explained by the chemical equilibrium theory. Assuming that the concentration of the LiBr solution remained constant throughout the ion-exchange reaction because of the large Li/Na ratio of 10:1, the equilibrium constant (K_T , Eq. 4) suggests that the Li/Na content does not change at a fixed temperature. According to the van't Hoff equation,³⁶ the equilibrium constant increases with the increase of temperature for endothermic reactions. In our case, increasing K_T requires an increase in x , which means an increase of the Li content of the exchanged phases with increasing temperature. For example, the Li content was stabilized at a certain value for each temperature region ($x = 0.63, 0.75, 0.92, 1.04, \text{ and } 1.16$ for $80^\circ\text{C}, 100^\circ\text{C}, 120^\circ\text{C}, 140^\circ\text{C}, \text{ and } 160^\circ\text{C}$, respectively; see Figure 4b). For practical purposes,

the Li content can be adjusted in the final ion-exchange product by controlling only the reaction temperature. Another striking feature of the composition diagram in Figure 4b is the large miscibility gap between the Na-rich and Li-rich phases independent of temperature, which is generally the same as that observed in the composition diagram in Figure 2e (at a series of LiBr concentrations in that case). Again, this finding suggests an abrupt change in the crystal structures at a certain Li content, below which only a solid solution is formed with limited Li being accommodated, maintaining the original tetrahedral structure with a space group of $P4_2/mnm$.

The temperature and LiBr molarity dependence of the Li content (x) and formation of the miscibility gap may not be solely explained by the kinetics of Li/Na interdiffusion in the bulk of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phases. These dependences may also arise from the limit of Li/Na ion-exchange at the solid/liquid and solid/solid interfaces between the Na-rich tetragonal phase ($P4_2/mnm$) and Li-rich orthorhombic phases ($Pnmm$ in the shell, as illustrated in Figure 2d). According to Fick's first law, the interdiffusion rate is determined by the concentration gradient and diffusion coefficient. Therefore, because of the large Na/Li concentration gradient and large diffusion coefficient in pure $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ (related to the low activation energy for Na hopping in the Na-rich phase, as discussed immediately below), at the beginning of the experiments, the ion exchange occurs instantaneously at the solid/liquid interface between the solid $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ and highly concentrated LiBr solution, leading to the formation of a Na-rich phase ($P4_2/mnm$) across the particle. As the reaction progresses, a Li-rich phase ($Pnmm$) will be first formed in the near-surface region (namely, the shell) around the Na-rich core because of the sluggish nucleation and growth of the new phase. Without direct contact with the LiBr solution, the ion-exchange rate of the Na-rich phase in the core is greatly reduced because of the lower concentration gradient at the solid/solid interface and the sluggish Na movement in the Li-rich phase. However, the ion-exchange rate in the Li-rich shell is relatively higher because of the high concentration gradient at the solid/liquid interface, which may have led to the miscibility gap of the composition, independent of LiBr concentration or temperature (Figs. S2g and 4b).

In the later stage of the ion-exchange process, the interdiffusion of ions in the solid became the rate-determining step,² as evidenced by the much slower reaction in the Li-rich solid-solution region (several hours) than in the Na-rich one (several minutes) shown in Figure 1b. It is presumed that the activation energy for Na hopping in the Li-rich phase ($Pnmm$) is much higher than that in the Na-rich phase ($P4_2/mnm$) because of both the lattice shrinkage ($\Delta V \approx -4.3\%$ for the full range of $0 < x < 1.5$; Supplementary Figure S5) and the distortion of the $Pnmm$ framework (Figure 3d–e). In fact, NEB calculations validated this hypothesis. It was observed that the activation energies for Na hopping in $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ ($x = 0$; $P4_2/mnm$) and $\text{Li}_{1.0}\text{Na}_{0.5}\text{VOPO}_4\text{F}_{0.5}$ ($x = 1.0$; $Pnmm$) were ~ 300 and ~ 1500 meV, respectively (Figure 4c–d). Therefore, we believe that Na^+ ions became more immobile as x reached 1.5, which made the Li^+/Na^+ ion-exchange process kinetically unfavorable. In principle, the slow Na diffusion at a high level of x can be overcome by increasing the temperature; however, the reaction temperature for the ion-exchange process is also limited by the stability window of the final product. Practically, this limitation of the temperature range is expected to result in the reaction stopping at a certain Li/Na composition even if a higher Li content is thermodynamically allowed by Eq. 4.

The Li content in the final product was not affected by the initial Li (in solution) to Na (in $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$) ratio (*i.e.*, the Li/Na ratio) for a given LiBr concentration as long as the ratio was higher than 2 (Supplementary Figure S1). This finding is in a good agreement with previous reports on the ion-exchange synthesis of layered oxides,¹⁸ in which the extent of the reaction was controlled by using insufficient Li/Na ratios. For $\text{P2-Na}_{2/3}[\text{Ni}_{1/3}\text{Mn}_{2/3}]\text{O}_2$, the fully ion-exchanged phase of $\text{T2-Li}_{2/3}[\text{Ni}_{1/3}\text{Mn}_{2/3}]\text{O}_2$ was obtained once the Li/Na ratio exceeded 2 despite the low concentration of Li (1 M).¹⁸ In our case, however, the reaction was not completed with 1 M solution even though we increased the Li/Na ratio up to 10:1, where only ~40% of Na^+ ions were replaced by Li^+ ions (Supplementary Figure S1). Instead, the Li content was mainly affected by the concentration of the Li^+ solution rather than by the amount of the Li^+ source (compared with the amount of $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ powders; *i.e.*, the Li/Na ratio). It is presumed that the Li/Na ratio can affect the Li content only if it is not high enough to maintain the initial LiBr concentration throughout the ion-exchange process. For compounds with relatively slow ion-exchange kinetics, as in this case, we expect that increasing the concentration of the Li solution will be more effective for obtaining a higher Li content than using an excessively high Li/Na ratio.

The Li content in the material did not decrease or increase when the LiBr solution was cooled down or diluted during the ion-exchange reaction, respectively, despite the strong concentration and temperature dependences (Supplementary Figure S14), implying the irreversibility of the reaction. This finding is attributed to the solubility of NaBr in the solvent being negligible compared with that of LiBr. We believe that a large solubility difference between two ion-exchanging cations is important for maximizing the content of the guest cation in the host crystal. Finding a combination of anion and solvent (*e.g.*, Br^- and 1-hexanol in our case) that provides a large solubility difference may be advantageous for developing a facile ion-exchange process.

Electrochemical Properties and Thermal Stability of Exchange Products

The insights gained from systemic *in situ* studies can be directly applied to designing efficient protocols for the exchange synthesis of new Li electrodes. For example, the Li substitution may be tuned by adjusting the synthesis parameters to optimize the electrode performance, as demonstrated in Figure 5a–b (for the synthesis of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$). The electrode with a maximum Li content of $x=1.34$ was obtained at 160°C (*via* a slow solid-solution process with sufficient exchange time and Li source) and exhibited superior electrode performance compared with electrodes with lower Li content ($x = 1.02$; shown in Figure S15). The performance of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ electrodes with Li contents below 1.0 is expected to be even worse because the $\text{V}^{4+}/\text{V}^{5+}$ redox couple can only be used partially in the Li-ion cells.

For $x = 1.34$, the reversible capacity at a C/10 rate was close to the theoretical value of 145 mAh g^{-1} (Figure 5a). Moreover, a high voltage of ~4 V (vs. Li^+/Li) was observed, leading to a high energy density of 580 Wh kg^{-1} . The rate capability and cyclability of the $x = 1.34$ electrode were excellent (Figure 5b). More than half of the theoretical capacity was maintained at a fast current rate of 20C despite the micron-sized particles. No significant capacity loss was detected after 100 cycles at a 1C rate (capacity retention of 94%; inset of Figure 5b), suggesting the high structural stability upon cycling. The superior electrochemical performance of

$\text{Li}_{1.34}\text{Na}_{0.16}\text{VOPO}_4\text{F}_{0.5}$ ($x = 1.34$), which was newly discovered in this work, makes it a promising candidate for high-power cathodes in LIB. The electrochemical properties of the $x = 1.02$ electrode (Supplementary Figure S15) were significantly inferior compared with those of the $x = 1.34$ electrode. The electrochemical tests demonstrated the strong dependence of the electrochemical properties on the extent of Li^+ exchange, and maximizing Li ion exchange appears to be essential to achieving high capacity as well as long-term cyclability. This finding is likely due to the enhancement of the structural stability with a close-to-complete replacement of Na^+ by Li^+ according to the structural analysis.

The thermal stability of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ was also investigated using temperature-resolved synchrotron XRD measurements, and the main results were presented in Figure 5c–d and Figure S16. Upon heating, the $x = 1.34$ phase underwent a phase separation into $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ and LiVPO_4F (or $\alpha\text{-LiVOPO}_4$) at an onset temperature of approximately 280°C, which is similar to the thermal decomposition of the $\text{Li}_{1.1}\text{Na}_{0.4}\text{VPO}_{4.8}\text{F}_{0.7}$ phase.¹⁶ Phase and thermal-stability diagrams for the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ system were constructed based on the temperature-controlled XRD data (Figure 5d; see Supplementary Figure S16 for XRD data of $x = 0.62$ and 1.02). The reversible phase transition into the phase $I4/mmm$ with higher-symmetry was detected for all the Li/Na compositions, and the onset temperatures were in the range of 200–250°C. Interestingly, there was a sudden drop in the phase decomposition temperature at $x \approx 1.0$, which should be considered when selecting the best composition in the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ system in terms of thermal stability. The increasing thermal instability with increasing Li content may be due to insufficient Na^+ ions, which are believed to act as pillars of the original framework. This finding suggests that obtaining a high Li content in the ion-exchanged phase is not always the best choice. Therefore, finding an optimal Li/Na composition that provides the best trade-off between the electrochemical and thermal properties is important for practical battery use of ion-exchanged compounds.

Ion Exchange in 1D Polyanionic *vs.* 2D Layered Compounds

As discussed above, the phase transformation was eventually induced by 1D ion transport along the *a* direction, which gave rise to the ordered repetition of Li, Na, and vacancy channels. The dynamic ion ordering with ion exchange led to changes in the lattice parameters (Figure 3f) and reduction of the tetragonal symmetry ($P4_2/mmm$) to orthorhombic symmetry ($Pnmm$). This finding appears to suggest that such a phenomenon of Li^+/Na^+ ion-exchange-induced phase transformation may not be unique to $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ but applicable to other polyanionic compounds (and beyond), wherever 1D ion transport occurs because of the intrinsic structural properties.

It is also noteworthy that two-phase transformation in polyanionic $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ differs significantly from that in layered compounds, where the stacking sequences of the two phases differ ($\text{P2-Na}_{0.7}\text{CoO}_2$ vs. O2-LiCoO_2 ; $\text{P2-Na}_{2/3}[\text{Ni}_{1/3}\text{Mn}_{2/3}]\text{O}_2$ vs. $\text{T2-Li}_{2/3}[\text{Ni}_{1/3}\text{Mn}_{2/3}]\text{O}_2$).^{18–20} In contrast, in this case, the two phases had no stacking sequence but different space groups ($P4_2/mmm$ for the Na-rich phase vs. $Pnmm$ for the Li-rich phase in $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$). We believe that this difference mainly originated from the flexibility of the framework (*i.e.*, the gliding ability of the layers) in layered Na_xCoO_2 . That is, the original prismatic Na sites can be converted into new octahedral sites for smaller Li^+ ions *via* simple gliding of the layers, whereas the pseudo-layered structure of

$\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ is difficult to slide because the layers are linked by anions (Figure 3b–e). Therefore, Li^+ ions introduced into $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ have no choice but to occupy the original prismatic Na sites, which are too large for Li^+ ions. It is presumed that this phenomenon led to the similar Li/Na ratios for different alkali-metal layers throughout the ion-exchange process, which implies the absence of a stacking sequence. However, the P2- and O2-phases observed in the ion-exchange reaction of Na_xCoO_2 were occupied solely by Na^+ and Li^+ ions, respectively,²⁰ because the prismatic sites of P2 stacking prefer Na^+ ions, whereas the octahedral sites of O2 stacking prefer Li^+ ions. Thus, only layers containing either Na^+ or Li^+ ions could be observed throughout the ion-exchange reaction. In another example, the Dahn group detected an intermediate phase of $\text{Li}_{1/3}\text{Na}_{1/3}[\text{Ni}_{1/3}\text{Mn}_{2/3}]\text{O}_2$ during the ion exchange of $\text{P2-Na}_{2/3}[\text{Ni}_{1/3}\text{Mn}_{2/3}]\text{O}_2$, and they concluded that the intermediate phase had alternating alkali-metal layers occupied by Li and Na.¹⁸ In our case, however, the alkali-metal layers in the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phases ($x = 0.62, 1.02, \text{ and } 1.34$) contained both Li^+ and Na^+ ions with comparable amounts, as demonstrated by the absence of splitting for the (002) reflection and the calculation results (Supplementary Figure S17). The lack of preference for a particular layer in Li occupation may allow the phase boundary between two phases ($P4_2/mmm$ vs. $Pnmm$) to form in any direction (unlike for 2D layered oxides), suggesting that the core-shell model was suitable for explaining the phase transformation within the particles. The ion-exchange kinetics of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ system are expected to be slower than those of layered oxides because of the slow Li/Na interdiffusion along the 1D channels in the Li-rich phase (Figure 4b) and sluggish phase propagation within the particles (Figure 2d).

The origin of the 1D Na array (Figure 3b–c) observed for $x = 0.62$ can be explained by comparison with the Na–vacancy ordering in the electrochemical reaction. Focusing on the short-range ordering, one can find a pair of Na^+ ions facing each other (*i.e.*, a Na dumbbell in Figure 3b). This type of Na configuration was also observed in an intermediate phase of $\text{Na}_{1.0}\text{VOPO}_4\text{F}_{0.5}$ during the electrochemical process of a $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ cathode in a Na cell.^{26,27} It was presumed that the dumbbell configuration effectively relieved $\text{Na}^+ \text{--} \text{Na}^+$ repulsion to stabilize the intermediate phase; this assumption may also be used to explain the formation of the similar Na dumbbells (Figure S10) in an intermediate phase of $\text{Li}_{0.5}\text{Na}_{1.0}\text{VOPO}_4\text{F}_{0.5}$ (Figure 1e). Interestingly, Na dumbbells were arranged in a line on the *ab* plane in $\text{Li}_{0.5}\text{Na}_{1.0}\text{VOPO}_4\text{F}_{0.5}$ of the ion-exchange reaction (anisotropic Na repulsion), whereas their long-range ordering was absent in $\text{Na}_{1.0}\text{VOPO}_4\text{F}_{0.5}$ of the electrochemical reaction (isotropic Na repulsion).^{26,27} This finding can explain the observation that the former had a rectangular unit cell in the *ab* plane ($Pnmm$), whereas the latter had a square one ($I4/mmm$)^{26,27} despite having the same framework and Na content. It is presumed that the Li^+ ions caused this difference as the rotation of Na dumbbells in $\text{Li}_{0.5}\text{Na}_{1.0}\text{VOPO}_4\text{F}_{0.5}$ may be restricted by adjacent Li^+ ions, whereas the Na dumbbells in $\text{Na}_{1.0}\text{VOPO}_4\text{F}_{0.5}$ are free to rotate. The Li occupation in the prismatic Na site can cause a local distortion, whose non-uniform distribution may destabilize the structure. We believe that the 1D Na array resulted from the uniform distribution of local distortions induced by Li^+ ions, as demonstrated by the periodic lattice distortion of the $x = 0.62$ phase (Figure 3b–c). This 1D Na array should be interpreted as a thermodynamic phenomenon rather than a snapshot during the ion-exchange process in which Li/Na

interdiffusion occurs along 1D channels because the ordering reversibly disappeared/appeared upon heating/cooling (*see* Supplementary Figure S12).

CONCLUSION

In summary, we unraveled the Li^+/Na^+ exchange process in the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ system ($0 \leq x \leq 1.5$) during solvothermal ion exchange in LiBr solution through a combination of time-resolved and temperature-resolved *in situ* synchrotron XRD measurements with *first-principles* calculations. In contradiction to the traditional belief of fast ion substitution through solid-solution reaction, an abrupt two-phase transformation, from a Na-rich tetragonal phase ($P4_2/mmm$) to a Li-rich orthorhombic phase ($Pnmm$), was observed at approximately $x = 0.5$. A core-shell model was proposed to explain the phase distribution and propagation within particles, thereby suggesting that Li^+/Na^+ exchange at liquid/solid and solid/solid interfaces in addition to ion interdiffusion within solids may eventually govern the exchange kinetics during the entire reaction process. Possible diffusion pathways for the ion-exchange process in 1D polyanionic compounds were also proposed based on the detailed structural analysis and compared with those in well-studied layered oxides.

The effects of various experimental parameters such as the concentration of the LiBr solution, reaction temperature, and Li/Na ratio were closely examined, thereby providing guidance to controlling the Li content in the exchanged products and thereby optimizing their structural and electrochemical properties. Excellent rate capability and cyclability were achieved in the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ electrode by maximizing the Li content, making it a promising candidate for high-power cathodes in Li-ion batteries. The results of this work shed light on the thermodynamics and kinetics of ion-exchange reactions for the synthesis of multi-Li polyanionic compounds. The *in situ* method developed in this study may be widely applied to the investigation of a wide range of solution-based syntheses, paving the way toward rational design of new battery electrodes and other energy materials.

ASSOCIATED CONTENT

Supporting Information

Ex-situ Synchrotron XRD patterns of final products of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ prepared at different conditions (LiBr concentration, Na/Li ratio, reaction time, temperature); *In situ* time-resolved XRD patterns during Li^+/Na^+ ion-exchange process of $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ at 160°C using various LiBr concentrations: 0.2 M, 0.5 M, 1 M, 3 M, and (e) 4 M; Calibration curve between cell volumes and Li contents (*x*) of final products of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$; The synchrotron XRD patterns of (a) $\text{Li}_{1.02}\text{Na}_{0.48}\text{VOPO}_4\text{F}_{0.5}$ ($x = 1.02$) and (b) $\text{Li}_{1.34}\text{Na}_{0.16}\text{VOPO}_4\text{F}_{0.5}$ ($x = 1.34$); Unit cell volumes of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phases observed during *in situ* experiments using different LiBr molarities (0.2, 0.5, 1, 2, 3, 4, and 5 M); Bright-field TEM images (left) and the corresponding SAED patterns (right) of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ powders for (a) $x = 0$, (b) $x = 0.62$, (c) $x = 1.02$, and (d) $x = 1.34$; The second XRD patterns (main peak region of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phases) after temperature reached 160°C during Li^+/Na^+ ion-exchange reactions of $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ with different LiBr concentrations (0.5–5 M); The XRD patterns at room temperature prior to the beginning of *in situ* measurements with different LiBr molar concentrations (0.5–5 M); The second XRD patterns (main peak region of NaBr phase) after temperature reached 160°C during ion-exchange reactions of $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$

with different LiBr molarities (0.2–5 M); Crystal structures of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phases projected along the c axis determined from first-principle calculations. Alkali ion configurations on the ab plane for (a) $x = 0.5$, (b) $x = 1.0$, and (c) $x = 1.5$ with the lowest formation; Composition (x) and temperature dependence of the $|a-b|$ value in the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phases; The synchrotron XRD patterns for (a) $x = 0.62$, (b) $x = 1.02$, and (c) $x = 1.34$ during the heating (red) and the subsequent cooling (blue); Time-dependent evolution of the fraction of the Na-rich and Li-rich phases in the two-phase region shown in Figure 4b in the text; *In situ* time-resolved XRD patterns upon cooling after the completion of the ion-exchange reaction at 160°C and 90°C using 5 M LiBr solution with a Li/Na ratio of 10:1; Galvanostatic charge/discharge curve (1st cycle) of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ electrode ($x = 1.02$) at a C/10 rate; Temperature-controlled XRD patterns of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phases for (a) $x = 0.62$ and (b) $x = 1.02$; The synchrotron XRD patterns of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ powders ($x = 0.62$, 1.02, and 1.34) prepared from *ex situ* experiments. Splitting of (002) reflection was not observed for all compositions; Lattice parameters, atomic positions, bond valence, from refinements of synchrotron and neutron diffraction patterns; Thermal expansion coefficients of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phases ($x = 0, 0.62, 1.02$, and 1.34).

The Supporting Information is available free of charge on the ACS Publications website.

AUTHOR INFORMATION

Corresponding Authors

Kirsuk Kang: matlgen1@snu.ac.kr

Feng Wang: fwang@bnl.gov

Author Contributions

The manuscript was written through contributions of all authors. All authors have given approval to the final version of the manuscript.

ACKNOWLEDGMENT

This work is supported by the U.S. Department of Energy (DOE) Office of Energy Efficiency and Renewable Energy under the Advanced Battery Materials Research (BMR) program, Contract No. DE-SC0012704. This work was also supported by IBS-R006-G1. Synchrotron X-ray and TEM measurements carried out at the Center for Functional Nanomaterials and the National Synchrotron Light Source, Brookhaven National Laboratory, were supported by the U.S. Department of Energy, Office of Basic Energy Sciences, under Contract No. DE-SC0012704.

REFERENCES

1. Clearfield, A. *Chem. Rev.* **1988**, 88, 125.
2. Helfferich, F. G. Ion exchange. *Courier Dover Publications* (1962).
3. Armstrong, A. R.; Bruce, P. G. *Nature*, **1996**, 381, 499.
4. Capitaine, F.; Gravereau, P.; Delmas, C. *Solid State Ionics*, **1996**, 89, 197.
5. Chen, H.; Hautier, G.; Ceder, G. *J. Am. Chem. Soc.*, **2013**, 134, 19619.
6. Chen, H.; Hautier, G.; Jain, A.; Moore, C.; Kang, B.; Doc, R.; Wu, L.; Zhu, Y.; Tang, Y.; Ceder, G. *Chem. Mater.*, **2012**, 24, 2009.

7. Delmas, C.; Braconnier, J.-J.; Hagenmuller, P. A. *Mater. Res. Bull.*, **1982**, 17, 117.
8. Delmas, C.; Olazcuaga, R.; Cherkaoui, F.; Brochu, R.; Leflem, G. *Comptes Rendus Hebdomadaires Des Seances De L Academie Des Sciences Serie C* **1978**, 287, 169.
9. d'Yvoire, F.; Pintard-Scrépel, M.; Bretey, E.; de la Rochère, M. *Sol. Sta. Ion.* **1983**, 9, 851.
10. Ellis, B.; Makahnouk, W.; Makimura, Y.; Toghill, K.; Nazar, L. *Nat. Mater.* **2007**, 6, 749.
11. Gaubicher, J.; Wurm, C.; Goward, G.; Masquelier, C.; Nazar, L. *Chem. Mater.*, **2000**, 12, 3240.
12. Kim, H.; Park, I.; Seo, D.H.; Lee, S.; Kim, S.W.; Kwon, W.J.; Park, Y.U.; Kim, C.S.; Jeon, S.; Kang, K. *J. Am. Chem. Soc.*, **2012**, 134, 10369.
13. Kim, J.; Kim, H.; Park, I.; Park, Y.-U.; Yoo, J.-K.; Park, K.-Y.; Lee, S.; Kang, K. *Energy Environ. Sci.*, **6**, 830-834 (2013).
14. Kim, J.; Kim, H.; Park, K.Y.; Park, Y.U.; Lee, S.; Kwon, H.S.; Yoo, H.I.; Kang, K. *J. Mater. Chem. A*, **2014**, 2, 8632.
15. Kim, S.-W.; Seo, D.-H.; Kim, H.; Park, K.-Y.; Kang, K. *Phys. Chem. Chem. Phys.*, **2012**, 14, 3299.
16. Park, Y.-U.; Seo, D.-H.; Kim, B.; Hong, K.-P.; Kim, H.; Lee, S.; Shakoov, R. A.; Miyasaka, K.; Tarascon, J.-M.; Kang, K. *Sci. Rep.* **2012**, 2, 704.
17. Paulsen, J.; Dahn, J. *Sol. Sta. Ion.* **1999**, 126, 3.
18. Paulsen, J. M.; Larcher, D.; Dahn, J. R. *J. Electrochem. Soc.*, **2000**, 147, 2862.
19. Kang, K.; Meng, Y.S.; Bréger, J.; Grey, C.P.; Ceder, G. *Science* **2006**, 311, 977.
20. Tournadre, F.; Croguennec, L.; Willmann, P.; Delmas, C. *J. Solid State Chem.*, **2004**, 177, 2803.
21. Gwon, H.; Kim, S.-W.; Park, Y.-U.; Hong, J.; Ceder, G.; Jeon, S.; Kang, K. *Inorg. Chem.* **2014**, 53, 8083.
22. Xu, M.; Xiao, P.; Stauffer, S.; Song, J.; Henkelman, G.; Goodenough, J. B. *Chem. Mater.* **2014**, 26, 3089.
23. Barker, J.; Gover, R. K. B.; Burns, P.; Bryan, A. J. *Electrochem. Solid-State Lett.*, **2006**, 9, A190.
24. Chihara, K.; Kitajou, A.; Gocheva, I. D.; Okada, S.; Yamaki, J.-i. *J. Power Sources*, **2013**, 227, 80.
25. Gover, R. K. B.; Bryan, A.; Burns, P.; Barker, J. *Solid State Ionics* **2006**, 177, 1495.
26. Park, Y.-U.; Seo, D. H.; Kwon, H.-S.; Kim, B.; Kim, J.; Kim, H.; Kim, I.; Yoo, H.-I.; Kang, K. *J. Am. Chem. Soc.* **2013**, 135, 13870.
27. Park, Y.-U.; Seo, D.-H.; Kim, H.; Kim, J.; Lee, S.; Kim, B.; Kang, K. *Adv. Funct. Mater.* **2014**, 24, 4603.
28. Sauvage, F.; Quarez, E.; Tarascon, J. M.; Baudrin, E. *Sol. Sta. Sci.* **2006**, 8, 1215.
29. Serras, P.; Palomares, V.; Alonso, J.; Sharma, N.; López del Amo, J. M.; Kubiak, P.; Fdez-Gubieda, M. L.; Rojo, T. *Chem. Mater.* **2013**, 25, 4917.
30. Serras, P.; Palomares, V.; Goni, A.; Gil de Muro, I.; Kubiak, P.; Lezama, L.; Rojo, T. *J. Mater. Chem.* **2012**, 22, 22301.
31. Serras, P.; Palomares, V.; Goñi, A.; Kubiak, P.; Rojo, T. *J. Power Sources* **2013**, 241, 56.
32. Shakoov, R. A.; Seo, D.-H.; Kim, H.; Park, Y.-U.; Kim, J.; Kim, S.-W.; Gwon, H.; Lee, S.; Kang, K. *J. Mater. Chem.*, **2012**, 22, 20535.
33. Xu, M.; Wang, L.; Zhao, X.; Song, J.; Xie, H.; Lu, Y.; Goodenough, J. B. *Phys. Chem. Chem. Phys.*, **2013**, 15, 13032.
34. Kingery, W. D. *Introduction to ceramics* (1960).
35. Tsirlin, A.A.; Nath, R.; Abakumov, A.M.; Furukawa, Y.; Johnston, D.C.; Hemmida, M.; von Nidda, H.A.K.; Loidl, A.; Geibel, C.; Rosner, H. *Phys. Rev. B* **2011**, 84, 014429.
36. Atkins, P. W.; De Paula, J. *Physical chemistry*, Oxford University Press, 10th edition. (2010).
37. Roisnel, T.; Rodríguez-Carvajal, J. *Mater. Sci. Forum*, **2001**, 378, 118.
38. Perdew, J. P.; Burke, K.; Ernzerhof, M. *Phys. Rev. Lett.*, **1996**, 77: 3865.
39. Anisimov, V. I.; Zaanen, J.; Andersen, O. K. *Phys. Rev. B*, **1991**, 44, 943.

40. Anisimov, V. I.; Aryasetiawan, F.; Lichtenstein, J. *Physics: Condensed Matter*, **1997**, 9, 767.
41. Blöchl, P. E. *Phys. Rev. B*, **1994**, 50, 17953.
42. Kresse, G.; Joubert, D. *Phys. Rev. B*, **1999**, 59, 1758.
43. Kresse, G.; Furthmüller, J. *Comp. Mater. Sci.* **1996**, 6, 15.
44. Van der Ven, A.; Thomas, J. C.; Xu, Q.; Bhattacharya, J. *Math Comput Simul.* **2010**, 80, 1393.
45. Henkelman, G.; Uberuaga, B. P.; Jonsson, H. *J. Chemical Physics*, **2000**, 113, 9901.
46. Malik, R.; Abdellahi, A.; Ceder, G. *J. Electrochem. Soc.* **2013**, 160, A3179.
47. Delmas, C.; Maccario, M.; Croguennec, L.; Le Cras, F.; Weill, F. *Nat. Mater.* **2008**, 7, 665.
48. Orikasa, Y.; Maeda, T.; Koyama, Y.; Murayama, H.; Fukuda, K.; Tanida, H.; Arai, H.; Matsubara, E.; Uchimoto, Y.; Ogumi, Z. *Chem. Mater.*, **2013**, 25, 1032.

FIGURES

Figure 1. *In situ* tracking of structural evolution in $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ during solvothermal Li^+/Na^+ exchange in LiBr solution of varying LiBr concentrations. (a) Schematic illustration of the experimental setup for *in situ* probing of ion exchange using synchrotron X-ray diffraction (XRD). (b) Time-lapse XRD patterns of intermediates ($\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$) during ion exchange at 160°C using 5 M LiBr solutions (see also Figure S2 for the data obtained at several other LiBr concentrations: 0.2, 0.5, 1, 2, 3, and 4 M). Zoom-in view of the patterns recorded in the early exchange stages was also provided in the inset, wherein the transition from 2-phase (blue) and solid solution (red) was shown by the evolution of the (111) and (002) peaks. In each of the Figures, the first XRD pattern was collected at room temperature (before heating). (c) Third XRD pattern obtained from the experiment using 2 M LiBr, with characteristic peaks indicating the coexistence of a Na-rich phase (labeled by circles) and Li-rich phase (triangles). (d) Evolution of the position of (002) peak extracted from the time-resolved XRD data for different LiBr concentrations as in (b) and Figure S2a-f, and corresponding phase transformations at different exchange stages, from two-phase (shaded in blue), to solid solution (red), and then no-change. The position of (002) peak (vertical axis) is directly related to Li content (x) in the exchanged intermediates, and its evolution with time was shown both for Na-rich phases (in the lower part of the graph; empty symbols) and Li-rich phases (in the upper part; filled symbols). (e) Energy diagram of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ system (*i.e.*, possible configurations as x varies between 0 and 1.5) predicated by DFT calculations.

Figure 2. Structure and local distribution of Na-rich/Li-rich phases in the exchanged $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ ($0 \leq x \leq 1.5$; LVO PF). (a) Synchrotron XRD pattern of $\text{Li}_{0.62}\text{Na}_{0.88}\text{VOPO}_4\text{F}_{0.5}$ and Rietveld refinement using the space group of $Pnnm$, with the red dots, black line, blue line, and green bars representing the observed data points, calculated pattern, difference, and Bragg positions, respectively. The high quality of refinement is demonstrated by the small difference (inset: enlarged view of $29-37^\circ$ region). (b) Comparison of the synchrotron XRD patterns for $x = 0$ (bottom) and $x = 0.62$ (top), revealing non-splitting of the reflection peaks with $h=k$ (indicated by black arrows) and clear splitting of those with $h \neq k$ (blue arrows) in the latter ($x = 0.62$) due to the reduction of structure symmetry. The inset shows the arrangement of PO_4 tetrahedra (purple) and VO_5F octahedra (cyan) for $x = 0$ ($P4_2/mnm$). (c) Representative bright-field TEM image from one single LVO PF ($x = 0.62$) particle and electron diffraction recorded from the particle (see also Figure S6 for the data from LVO PF particles for $x = 0, 1.02$, and 1.34). (d) Illustration of Na-rich phase ($P4_2/mnm$) and Li-rich phase ($Pnnm$) as a function of Li concentration (x ; top) and schematic diagram of the sequence of ion-exchange steps based on the proposed core-shell model (bottom).

Figure 3. Ionic ordering and transport in $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$. (a) NPD pattern from $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ ($x = 0.62$) powder and Rietveld refinement using the space group of $Pnnm$, with the red dots, black line, blue line, and green bars representing the observed data points, calculated pattern, difference, and Bragg positions, respectively. The Bragg positions of an impurity phase of Li_3PO_4 ($Pmn2_1$; approximately 10.6(2) wt%) are denoted by magenta bars. (b) Arrangement of PO_4 tetrahedra and VO_3F octahedra in the ab plane for $x = 0.62$ ($Pnnm$) based on the refinement results. The atomic positions and occupancies of Na and Li sites were determined from NPD data (Table S8). The dashed circles labeled 1, 2, 3, and 4 denote Na1/Li1, Na2/Li2, Na3/Li3, and Na4/Li4 sites, respectively. Na^+ and Li^+ ions are denoted by orange and green spheres, respectively. The green arrows passing through empty Na3/Li3 sites represent empty channels. Na dumbbells are denoted by dashed ellipses. (c) Crystal structure of the $x = 0.62$ phase projected along the a direction. The red circle, blue square, and dashed circle denote the 1D Na array, Li channel, and empty channel along the a axis, respectively. Distribution of Na and Li sites in the ab plane of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ phases when (d) $x = 1.02$ and (e) $x = 1.34$. The 1D Na arrays consisting of Na1/Li1 and Na4/Li4 sites are still observed for $x = 1.02$ (dashed boxes). The Na3/Li3 sites are nearly empty, providing channels for ionic transport (green arrows). (f) Evolution of the lattice difference between parameters a and b ($|\Delta(a-b)|$) as a function of Li content (x). The lattice difference was reduced by a temperature-induced phase transition from $Pnnm$ to $I4/mmm$, as indicated by the blue curve.

Figure 4. Evolution of the structure with temperature and correlated ion diffusivity in $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ during Li^+/Na^+ exchange. (a) Temperature-controlled *in situ* XRD patterns during ion exchange using 2 M LiBr solution with a Li/Na ratio of 10:1. The temperature was elevated with a 20° step and then remained constant until the evolution of the XRD patterns became negligible. (b) The evolution of the Li content in the Na-rich ($P4_2/mnm$; bottom) and Li-rich ($Pn\bar{m}$; top) phases of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ as a function of the scan number (or reaction time). Here, the Li content was determined using the calibration curve in Supplementary **Figure S3**. (c) Schematic illustration of the Na diffusion path in the $\text{Li}_{1.0}\text{Na}_{0.5}\text{VOPO}_4\text{F}_{0.5}$ framework predicted using the NEB method. (d) Activation energy curve for Na hopping in $\text{Li}_{1.0}\text{Na}_{0.5}\text{VOPO}_4\text{F}_{0.5}$ ($Pn\bar{m}$, red) along the trajectory shown in (c) compared with that in $\text{Na}_{1.5}\text{VOPO}_4\text{F}_{0.5}$ ($P4_2/mnm$, blue) and $\text{Na}_{0.5}\text{VOPO}_4\text{F}_{0.5}$ ($I4/mmm$, black) from a previous report.²⁶

Figure 5. Electrochemical properties and thermal stability of exchanged products. (a) Galvanostatic charge/discharge curves (for the first two cycles) of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ electrode ($x = 1.34$) at a C/10 rate. The inset shows the dQ/dV curve for the first cycle. (b) High rate capability demonstrated by the capacity retention at a series of rates (up to 20C) and long cycling stability (inset) at 1C of the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ electrode ($x = 1.34$). (c) Thermal stability of $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ ($x = 1.34$) demonstrated by temperature-controlled synchrotron XRD data (data for $x = 0.62$ and 1.02 phases were presented in Figure S16). (d) Phase and thermal-stability diagrams for the $\text{Li}_x\text{Na}_{1.5-x}\text{VOPO}_4\text{F}_{0.5}$ system. The data for $x = 0$ were obtained from Ref. [35]

TOC