BNL-114453-2017-JA

File # 95452

**Electric field effect on chemical and phase equilibria
in nano-TiB₂-TiO₂-TiBO₃ system at < 650 degrees C:
an in situ time-resolved energy dispersive x-ray
diffraction study with an ultrahigh energy synchrotron probe**

T. E. Özdemir, Z. Zhong

Submitted to: Journal of Materials Research

January 1, 2017

Photon Sciences Department

Brookhaven National Laboratory

**U.S. Department of Energy
USDOE Office of Science (SC),
Basic Energy Sciences (BES) (SC-22)**

Notice: This manuscript has been authored by employees of Brookhaven Science Associates, LLC under Contract No. DE- SC0012704 with the U.S. Department of Energy. The publisher by accepting the manuscript for publication acknowledges that the United States Government retains a non-exclusive, paid-up, irrevocable, world-wide license to publish or reproduce the published form of this manuscript, or allow others to do so, for United States Government purposes.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or any third party's use or the results of such use of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Electric field effect on chemical and phase equilibria in nano-TiB₂-TiO₂-TiBO₃ system at < 650 degrees C: an in situ time-resolved energy dispersive x-ray diffraction study with an ultrahigh energy synchrotron probe

T. E. Özdemir¹, E. K. Akdoğan^{1,α}, İ. Şavklıyıldız¹, H. Biçer¹, M. Örnek¹, Z. Zhong², T. Tsakalakos¹

¹Dept. of Materials Science and Eng'g, Rutgers University, Piscataway, NJ 08854-8065, USA.

²National Synchrotron Light Source, Brookhaven National Laboratory, Upton, NY 11973, USA.

ABSTRACT

Titanium diboride (TiB₂) is a high strength ceramic which is considered for use in military armor applications. It is an excellent electrical and thermal conductor. However, TiB₂, as a highly covalent ceramic, is challenging to sinter to high densities while suppressing its oxidation. In this study, the effects of simultaneously applied electric and thermal fields on phase transformation in pre-oxidized TiB₂ nanoparticles (containing ≥20% oxide) was studied using in-situ time-resolved high temperature EDXRD with a polychromatic 200 keV synchrotron probe. Firstly, we report on the oxidation and phase transformation process in pre-oxidized TiB₂ in a temperature range (RT-600 °C) with no applied electric field where no further oxidation or phase transformation was observed. Secondly, we report on effects of two different magnitudes of applied electric field where we observed a sharp increase in the apparent conductance of the system at 520 °C under 16 V/cm and at 305 °C under 40 V/cm. Argon gas flowing of 4 psi pressure was used to establish the inert atmosphere. We observe an electric field facilitated oxidation and phase transformation in TiB₂ of ≥20% oxide used in this study at <600 °C. The process under applied electric fields yield TiBO₃ peaks almost instantaneously. An abnormal unit

cell dilation with the current draw is observed due to charge transport which phenomena is accompanied the oxidation and phase transformation in the system.

^aCorresponding author's e-mail: eka@rci.rutgers.edu

I. INTRODUCTION

Titanium diboride (TiB_2 hereafter) is a covalent ceramic with a hexagonal unit cell symmetry (space group $P6/mmm$).¹ It is a very compelling material for use in applications requiring high strength and superior abrasion resistance in the civilian and military technological realms because it exhibits a modulus of elasticity of $E = 565 \text{ GPa}$ at 298 K , a temperature coefficient $(dE/dT) = -0.032 \text{ GPa/K}$, and an ultrahigh Vicker's hardness ($25\text{-}34 \text{ GPa}$ at 298 K).^{2, 3} It is also considered as an effective neutron absorber.⁴ In addition, TiB_2 's ultrahigh melting temperature ($T_m = 3225 \pm 20 \text{ }^\circ\text{C}$)⁵ makes it a material of interest for high temperature applications.⁶⁻⁹ Moreover, TiB_2 is being used extensively as an electrode material in electrolytic processing of aluminum because of its chemical inertness against aluminum.⁹ This material is also used as an additive to obtain fine grain size aluminum castings because of its surface thermodynamic compatibility with aluminum, and low solubility in molten aluminum.¹⁰ Besides, it is a good metallic conductor ($\sim 15 \times 10^{-6} \Omega\text{cm}$ at 298 K) and a good thermal conductor ($96 \text{ W/m}\cdot\text{K}$ at 298 K).¹¹

The major issue with TiB_2 is its poor sinterability because of its low self-diffusivities associated with covalently bonded ceramics and its high tendency for oxidation. Generally, commercial submicron TiB_2 powders contain $\sim 2 \text{ wt}\%$ oxygen, whereas coarser powder has typically $\sim 1 \text{ wt}\%$ oxygen in solid solutions.¹² Surface oxidation due to residual oxygen is typically considered to be the root cause of accelerated grain coarsening and poor sinterability of TiB_2 .¹³ An earlier work¹⁴ on TiB_2 has established that residual oxygen is partitioned between the titanium and boron forming their respective oxides, i.e. TiO_2 and B_2O_3 . Therefore, sintering aids,

such as carbon, are preferred to ensure the proper reducing conditions during sintering process whereby oxidation of TiB_2 can be prevented.^{12, 13}

Polycrystalline TiB_2 can be densified to near full density by utilizing a plethora of processing methods, including conventional sintering,^{15–19} hot pressing,²⁰ hot isostatic pressing,^{16, 17, 21–23} microwave sintering,²¹ and dynamic compaction²⁴. The aforementioned low self-diffusivities of the constituent ions requires a densification temperature of approximately 2000 °C ($\sim 2/3 T_m$ where $T_m = 3225 \pm 20$ °C^{25–27}). However, such high densification temperatures also favor grain growth, and the anisotropy of the hexagonal grain structure results in internal stresses ultimately lead to spontaneous micro cracking during cooling. Grain growth can be limited, and densification can be enhanced by the use of sintering aids such as Cr, CrB_2 , C, Ni, NiB, and Fe.^{28–30} By the use of such densification aids (1-10 wt%), the densification temperature can be reduced to 1700-1800 °C and the densification time to ~ 60 minutes. Moreover, TiB_2 with Ni additive can be sintered to higher densities by hot pressing it at temperatures as low as 1425 °C for 2-8 hours.²⁰

Recently, it has been demonstrated that ceramic materials can be hot consolidated at temperatures typically 30-70% less than their conventional densification temperatures and at unprecedented time scales that are 1-2 orders of magnitude smaller than conventional densification times by a process called flash sintering³¹ (FS hereafter) or burst mode densification³² (BMD hereafter). For instance, it has been shown that yttria stabilized tetragonal zirconia can be fully densified in 5s at 850°C under the application of a nominal 120 V/cm dc electric field (conventional sintering temperature is $>1200^\circ\text{C}$), and this method was named as

flash sintering.³¹ The said densification process was successfully applied to Co_2MnO_4 , $\text{Ce}_{0.8}\text{Gd}_{0.2}\text{O}_{1.9}$ as well as MgO doped Al_2O_3 systems,^{33–35} and recently, BMD was demonstrated for B_4C where densification to $\geq 95\%$ ρ_{th} was achieved in ~ 324 seconds at 711°C under an applied field of 45 V/cm .³⁶ Here, there is a negligible contribution from Joule heating.³⁷ At this point, what is known is that the simultaneous application of thermal and electric fields causes a complex electromigration process whereby high density achieved in the form of a burst phenomenon which is completely absent under zero electric field.³²

It follows from the preceding elaboration on the properties of TiB_2 that the successful BMD processing of TiB_2 ceramics depends strongly on the mode and manner in which the material responds to the superimposed applied thermal and electric fields. Although there are some reports on the oxidation behavior of TiB_2 in the literature,^{12, 13, 38–43} one is deprived of studies focusing on electric field induced oxidation in this material which is what this study attempts to remedy by bringing in-situ time-resolved ultrahigh energy dispersive x-ray diffraction to bear. By elucidating the simultaneous electric and thermal field response of TiB_2 , we hope to provide a quantitative description of the prerequisite conditions needed for its BMD.

This article is organized as follows: In Section II, we give a detailed account of the experimental method used in this study since there is no precedent for the experimental approach reported here. The experimental results are presented in Section III where we describe the electric field driven and thermally facilitated evolution of the multiphase equilibria and provide a thermokinetic analysis. We conclude the article with Section IV where speculate on possible future directions in this line of research.

II. EXPERIMENTAL

The present study was carried out at the superconducting wiggler beam line X17-B1 of the National Synchrotron Light Source (NSLS) of Brookhaven National Laboratory (BNL), Upton, New York. We have used polychromatic radiation with photon energies as high as 200 keV for this in situ ultrahigh EDXRD study. The high photon energies enabled us to collect data with a time resolution (Δt hereafter) of as frequent as 2 seconds which is otherwise not possible with conventional Bragg-Brentano laboratory or soft x-ray synchrotron techniques. Figure 1a³² depicts a schematic illustration showing the particulars of the diffraction technique we brought to bear in this study. The technique involves an ultrahigh energy polychromatic incident radiation that is scattered at a fixed Bragg angle and measured by a germanium detector.^{44, 45} The incident and scattered beam collimating slit openings, and the fixed Bragg angle (1.5° in this study) define the so-called gauge volume (GV hereafter). The said GV is translated into the specimen and placed at the body center of the specimen at which point it becomes the diffraction volume. In other words, the said technique is essentially a transmission method (Laue mode⁴⁶) where the specimen under test is stationary and so is the diffraction volume.⁴⁷ An in-house custom-made hot stage (HS hereafter) illustrated in Figure 1b³² was used to heat the sample while a dc electric field was applied to it in the parallel plate geometry.³² The HS is comprised of a spring loaded ceramic (insulator) specimen holder that is resistively heated and to which leads are attached to apply the electric field. The said HS enclosure is mounted on the positioning stage and exposed to the beam (see Fig 1³²).

Commercial TiB_2 powder⁴⁸ of 58 nm primary particle size as reported by the manufacturer (US research nanomaterials, Inc) and 125 nm median aggregate size (secondary) as measured by laser diffraction was uniaxially pressed into disks of 12 mm diameter and ~2.5 mm thickness under 4 tons without using binder. SEM image of as received powder is seen in Figure 2. Typical as-pressed density of such specimens was ~%50 of the x-ray density.

In the first part of this experimental study, a TiB_2 specimen of ~2.5 mm thickness was heated with a ~20 °C/min average heating rate under zero electric field until its temperature reached 600 °C during which data was collected with a $\Delta t = 3$ seconds kinetic. In the second part of the present study, two TiB_2 specimens of ~2.5 mm thickness were heated with a ~20 °C/min average heating rate under an applied dc electric field of 16 V/cm and 40 V/cm. Maximum temperature till which each experiment was carried out was ~600 °C. The temperature and current leakage of each specimen were monitored. Data was collected with 3 seconds and 2 seconds time interval for the experiments performed under lower and higher electric field, respectively. Each specimen was left to cool to room temperature under zero field after the temperature reached its maximum while data collection was continues with Δt . All experiments were carried out in an inert atmosphere. Also, we have collected x-ray spectra at the beginning and after the completion of each experiment at RT to establish the net footprint of the thermal and/or electrical cycle to which the specimens were subjected.

Theoretical temperature limits to which each specimen can reach if we assume 100% electric to heat conversion, which assumption actually defeats the thermodynamics' second law and so is impossible to be true, and no heat loss during the burst event in each experiment are

calculated using the collected voltage and current data. Power curve, as a function of time, is integrated, and the work done by electric field during the burst event during which the most of oxidation and phase transformation works are done. The equation used in the calculations are as follows;

$$W = n \int_{T_0}^{T_f} C_P^{TiB_2} dT + n \int_{T_0}^{T_f} C_P^{TiO_2} dT + n \int_{T_0}^{T_f} C_P^{TiBO_3} dT \quad (1)$$

where W is the work done by applied electric field, n is molar value, C_P is specific heat equation of each material, T_0 is the temperature at which the burst event starts, and T_f is the final temperature value if the aforementioned assumption is the case. Because TiB_2 powder used for this study contains considerable amounts of oxide phases, these oxide phases are also included in the calculations. Approximate molar value of each crystalline phase in a TiB_2 sample is 0.0043, 0.0020, and 0.00123 for TiB_2 , TiO_2 , and $TiBO_3$ at RT, respectively. Due to the lack of information on $TiBO_3$ in the literature, average of Eq. 2⁴⁹ and 3⁴⁹ was used as its specific heat equation (Eq. 4).

$$C_P^{TiB_2} = 56.379 + 25.857 * 10^{-3} * T - 1.745 * 10^6 * T^{-2} - 3.347 * 10^{-6} * T^2 \quad (2)$$

$$C_P^{TiO_2} = 73.346 + 3.054 * 10^{-3} * T - 1.703 * 10^6 * T^{-2} \quad (3)$$

$$C_P^{TiBO_3} = 64.8625 + 14.4555 * 10^{-3} * T - 1.724 * 10^6 * T^{-2} \quad (4)$$

In closing this section, we provide the governing EDXRD equation, which was used in the ensuing analysis of the data, for continuity and completeness as follows: The Bragg's law⁵⁰

$n\lambda=2d_{hkl}\sin\theta_{hkl}$ (here n is the order of reflection and λ the wavelength of the radiation) is combined with the Planck-Einstein equation⁵¹ $E=h\nu$ where $\nu=c/\lambda$ (here ν is the linear frequency) and setting $n=1$, from which one obtains;

$$\frac{1}{d_{hkl}} = \left(\frac{2 \sin \theta_{hkl}}{hc} \right) E_{hkl} = |Q_{hkl}| \quad (5)$$

where d_{hkl} is the interplanar spacing of the atomic plane with Miller indices (hkl) , θ is the Bragg angle (1.5° in this study), h is the Planck's constant (6.626×10^{-34} J·s), c is the speed of light (2.9979×10^8 m/s), E_{hkl} is the scattered energy from lattice plane (hkl) , and $|Q_{hkl}|$ is the magnitude of the reciprocal lattice vector pertaining to (hkl) in real space. Here, E_{hkl} is the measured quantity, which is equivalent to measuring the magnitude of the reciprocal lattice vector Q_{hkl} directly, thereby enabling one to determine d_{hkl} with great accuracy. The energy calibration was accomplished by using Ag, Au, Cu, CeO₂, TiO₂, and LaB₆ (NIST SRM 660) standards.⁵² The patterns were cross checked against the Powder Diffraction Database by which qualitative x-ray phase analysis was accomplished. The collected patterns were then indexed, and the hexagonal lattice constants (a and c) of the TiB₂ were computed.^{53–55}

III. RESULTS AND DISCUSSION

No new peak on the spectra of TiB₂ occurred when the sample was heated under zero electric field. A little shifting in the position of TiB₂ (001) peak was observed that it might be an indicative of the fact that this peak turned into TiO₂ (110). Observed TiBO₃ peak of very low intensity at the beginning of the experiment completely disappeared at $\sim 160^\circ\text{C}$. Figure 3 depicts the synchrotron energy dispersive x-ray diffraction spectra of the sample at different temperature values.

Oxidation behavior of TiB_2 under an applied dc electric field of 16 V/cm as well as a thermal field is as in Figure 4. As soon as the sample becomes conductive at $\sim 520^\circ\text{C}$ within 23.6 minutes, and current starts flowing through the sample, TiBO_3 (012) peak starts showing up on the spectrum, and its intensity increases to 100 a.u., which is almost 2/3 of the intensity of TiB_2 (100) (the most intense TiB_2 peak), in less than a minute. Given the fact that the intensities of the same peaks obtained using EDXRD and powder x-ray diffraction do not always match, the most intense peak on a spectrum may also vary, as we observed in our experiments, that though the most intense TiB_2 peak should be TiB_2 (101),⁵³ the spectra we obtained has revealed that it was TiB_2 (100) in our experiments. Therefore, interplanar spacing is mostly taken as the major reference point to identify a peak on an EDXRD spectrum. TiBO_3 (104) peak appears on the spectrum after TiBO_3 (012), but its intensity increases faster than that of TiBO_3 (012) and reaches ~ 150 a.u. in 30 seconds. The intensities of TiBO_3 (113) and TiO_2 (101), which are already present at RT prior to the experiment, do not change much compared to the newly forming oxide phases. TiBO_3 (104) is the strongest peak followed by TiBO_3 (012) according to the literature.⁵⁵ In other words, TiBO_3 (104) and TiBO_3 (012) are 100% and 64.6% peaks, respectively.⁵⁵ In our experiment, though the TiBO_3 (104) formed later, their intensities reached almost the same value and changed equally from the moment current flow stabilized onward. Two different current leakage stage was observed under the influence of 16 V/cm dc electric field. The current reached 4.5 A in the first burst and then showed a little decrease, and the second burst occurred 760 seconds later the first one (see Fig. 10), as a result of which the current draw showed a rise to 4 A. Thus, the intensity of the oxide peaks reached their

maximums (Fig 7). TiB_2 (100) peak also exhibited a bit rise in intensity right after the first burst though no drastic change was observed due to the second one.

Figure 5 depicts the effect of 40 V/cm electric field on TiB_2 . The specimen becomes conductive at $\sim 305^\circ\text{C}$ within 14 minutes. Once the material lets the current leakage as a result of increasing temperature and the electric field, TiBO_3 (012) peak occurs on the EDXRD spectrum followed by the formation of TiBO_3 (104). Intensity of TiBO_3 (012) increases to 70 a.u. within the first 20 seconds, whereas that of TiBO_3 (104) exhibits a sharp increase and reaches ~ 150 a.u. in 16 seconds. Current leakage exhibits a steep rise and reaches 10 A followed by a bit drop and a sudden increase to 10 A again which results in 2 different bursts occurring in shorter time spans compared to the experiment under the application of 16 V/cm. The intensity of TiB_2 (100) peak increases with the current flow as well. Maximum intensity value the TiBO_3 (104) peak reaches is ~ 450 a.u. while TiB_2 (100) can only reach ~ 340 a.u. maximum intensity. These results reveal that TiBO_3 phase dominates the system upon an applied dc electric field.

Evolution of the new phases under nominal electric fields of 16 V/cm and 40 V/cm is demonstrated in Figure 6. The effects of the applied electric fields of different magnitudes on the development of new oxides can be clearly seen in this figure.

Figure 7 shows the quantitative analysis results of the experiments conducted under electric fields. As seen in the figure, amount of TiBO_3 phase increases with a sudden rise in the current leakage. This figure exhibits that the phase transformation between oxides occurs slowly and takes longer time under 16 V/cm than that under 40 V/cm. Figure 7a, pertaining to lower electric field, reveals that phase composition of TiBO_3 increases from 24% to 31% in ~ 50

seconds due to the first burst of charges. After that, the amount of TiBO_3 in the system keeps increasing slowly. Once the temperature reaches 590°C , current leakage shows a sudden rise again. Therefore, the second burst and hence the second instantaneous increase in the phase composition of TiBO_3 occur as seen in the figure. While the phase composition of TiBO_3 increases, that of TiB_2 and TiO_2 decreases due to chemical reactions in the system. Phase composition of TiO_2 decreases from 27% to 22% in ~ 50 seconds and keeps decreasing slowly with an increase in the temperature up to 590°C where another instant decrease in its composition takes place. TiB_2 shows not a drastic change in its composition due to the first burst, but the effect of the second burst on it can clearly be seen in the Figure 7a. Figure 7b exhibits the effect of 40 V/cm on the specimen as a sharp change in the compositions of TiBO_3 and TiO_2 . The composition of TiBO_3 increases from 18% to 38% in 38 seconds. Then, it keeps increasing as the current keeps flowing through the sample. TiBO_3 exhibits another sudden increase in its composition due to the second burst of charges which is much less than the first one. On the other hand, TiO_2 shows a drastic decrease in its composition upon the burst events. It decreases from 32% to 12% as a result of the first burst and keeps decreasing slowly till the second burst where it completely decomposes. Aside the drastic changes in the compositions of oxides, TiB_2 is affected by each burst less than oxide phases as seen in the figure.

The response of nano- TiB_2 system to the applied thermal field is illustrated in Figure 8. As seen in the figure, no surprising singularity is observed in the system in a range of RT - 600°C . The ultimate expansion in the unitcell volume is 0.95% in ~ 28.5 minutes. The expansion was linear, and the coefficient of thermal expansion was found to be $6.60 \times 10^{-6}\text{ K}^{-1}$ and $9.28 \times 10^{-6}\text{ K}^{-1}$ for a and c , respectively.

Figure 9a emphasizes the effect of 16 V/cm electric field on nano-TiB₂ system at unitcell scale. Ambiguities observed during thermal expansion where thermal field is dominant over electric field is due to small changes in the heating rate. Expansion in the unitcell volume is 1.17% (in ~23.5 min) before the current passes through the sample. Specimen lets the current draw reach from 0.1 A to 4.5 A at 520 °C, and unit cell volume anomalously expands. Furnace temperature reaches 560 °C within 150 seconds. Total unit cell volume dilation is 0.6% due to the first burst. 0.43% expansion in the unit cell volume is adiabatically done by the first burst of the charges in ~50 seconds. The following 0.17% of the total 0.60% first abnormal expansion might be due to the Joule heating as well as some other additional processes, such as electromigration, in the material. As for the second burst, expansion in the unit cell volume is 0.41%. However, because this event takes longer time (≥ 200 seconds), the effect of the Joule heating in this stage of the experiment might be more. Difference between current values during the first and second anomalous unit cell volume expansions is also of significance. In the first burst of the charges where the material completely became conductive for the first time, the current leakage reached 4.5A and then decreased and stayed almost stable till 590 °C temperature value. It was 2.5A at this point. The second burst which yielded ~ 0.41% dilation in the unit cell volume occurred at this temperature value as a result of the second sudden rise in the current leakage from 2.5A to 4A. Figure 9b shows the spontaneous response of the unitcell volume to 40 V/cm dc electric field. The specimen on which 40 V/cm electric field is imposed becomes conductive at < 300 °C, and the burst of the charges takes place at 305 °C as a result of which the unit cell volume exhibits an abnormal expansion. Moreover, it expands in a steady state by 1.12% in 873 seconds from RT to 305 °C under the effect of largely thermal field;

however, the sudden rise in the current leakage from 0.1 A to 10 A within 38 seconds triggers an abnormal dilation in the unit cell volume by 1.42% as seen in the figure. Another abnormal increase in the unit cell volume occurs 199 seconds later the first burst, but the magnitude of the second expansion, 0.38%, is much lower than the first one. Because the second anomalous expansion follows a more linear behavior and takes more time compared to the first one, it might mostly be a result of Joule heating. Furnace temperature after the second burst event reaches 458 °C. The system is started to be cooled down at <500 °C.

Figure 10a depicts the changes in the power imposed on the specimen under 16 V/cm electric field. Because all experiments were carried out in current control mode, power source used for this study adjusted the voltage itself depending on the response of the material to the applied field. As seen in the figure, there are three stages occurring under thermal and electric fields which are named as incubation, onset, and burst during which the oxidation takes place. No electric field is observed in the incubation stage. In the onset stage, the material becomes conductive, but the current the sample receives is not high enough to instigate densification (in most materials) or phase transformation and oxidation (in TiB₂ containing significant amount of oxygen). In the burst stage, the current and hence, the power increases to its maximum in a very short time. The most of the work of phase transformation and oxidation is done in this stage. The current jumps from 0.12 A to 4.5 A in 51 seconds, and hence, the power rises from ~0.5 W to 18 W. Integration of the area highlighted by yellow color in Figure 10a yields the work (124.392 Joule) done by 16 V/cm electric field. This calculation assumes 100% electric to heat conversion, which actually defeats the second law of thermodynamics, and no heat loss as mentioned earlier. The upper internal temperature limit is found to be 740 °C based on the solution of Equation 1.

Changes in the power imposed on the specimen under 40 V/cm is depicted in Figure 10b. The burst event starts at 305 °C, and it takes 38 seconds for the current to reach its maximum of 10 A. The onset begins at 280 °C till which no current flow is observed in the system. The power on the specimen increases from ~0.6 W to 100 W with the sudden rise in the current leakage, so that the most of the work for phase transformation between the oxides is done in this time span. The work done by 40 V/cm during the burst event is 297 J, and the internal temperature limit is calculated as 842 °C following the same steps as in the case of 16 V/cm.

Given the fact that the powder we used contain TiO₂, TiBO₃, and B₂O₃ (in amorphous form) in addition to host TiB₂ particles, possible reactions which the applied electric field triggers are as follows;

These reactions are also in line with the reactions Kulpa et al. suggested in their study.¹² Second reaction might be taking place under lower electric field more compared to higher electric field because the quantitative analysis of phase composition in the samples reveal that TiB₂ is more involved in lower field experiment (Figure 7a). A tentative model exhibiting the oxidation of a TiB₂ particle is seen in Figure 11. This model suggests the following steps;

- (i) Diffusion of O₂ in ambient atmosphere
- (ii) Dissolution of O₂ at interface (1)

- (iii) Diffusion of O₂ in oxygen layer
- (iv) Chemical reaction of O₂ with TiB₂ passing interface (2)

We conclude that the resistivity of TiB₂ samples decreases over <500 °C and 640 °C and <300 °C and 458 °C temperature ranges, under 16 V/cm and 40 V/cm, respectively, per $J = (1/\rho)E$ where J (i/A)⁵⁶ is the current density and E (V/t) is the electric field intensity as A and t being cross sectional area and thickness of the sample, respectively. The work done by thermal and electric fields as a result of sudden rise in the current leakage yields a density increase by only 10% (maximum density of ~60% based on Archimedes technique) in each sample. It is so because of the poor sinterability of TiB₂^{12, 57} as well as its high tendency to oxidation^{12, 13, 41–43, 58–60}.

IV. CONCLUDING REMARKS

We have shown the effects of an applied electric field of a chosen magnitude on the phase transformation in nano-TiB₂ system containing a considerable amount of oxygen ($\geq 20\%$ at RT) and the fact that it is accompanied the abnormal unit cell expansion. The dominant phase forming upon the applied electric field is TiBO₃. The higher the electric field results in the earlier reactions which yield new oxide phases. Possible reactions taking place in the system with the application of an electric field are;

The tentative model we have proposed for the oxidation of TiB_2 obeys the following steps;

- (i) Diffusion of O_2 in ambient atmosphere
- (ii) Dissolution of O_2 at interface between the ambient atmosphere and oxide layer
- (iii) Diffusion of O_2 in oxygen layer
- (iv) Chemical reaction of O_2 with TiB_2 passing interface between the oxide layer and a TiB_2 particle

Since the calculated internal temperature limit, especially the one under higher electric field, is a lot higher than the measured furnace temperatures, there might be some other mechanisms triggered by the applied electric fields, such as electromigration and diffusion of oxygen vacancies, in addition to some Joule heating.

Acknowledgments

The authors wish to express their gratitude for the financial support provided by the Office of Naval Research (ONR) under Contract No. N00014-10-1-042. The authors wish to thank Dr. L. Kabacoff of the ONR for his valuable technical feedback and support of this project. T.E.Ö. acknowledges the support from the Turkish Ministry of Education. This research was carried out in part at the National Synchrotron Light Source (NSLS), a U.S. Department of Energy (DOE) Office of Science User Facility operated for the DOE Office of Science by Brookhaven National Laboratory under Contract No. DE-AC02-98CH10886.

References

- ¹ D. Vallauri, I.C.A. Adrián, and A. Chrysanthou, “TiC–TiB₂ composites: A review of phase relationships, processing and properties,” *J. Eur. Ceram. Soc.*, **28** [8] 1697–1713 (2008).
- ² M. Ziemnicka-Sylwester, “TiB₂-Based Composites for Ultra-High-Temperature Devices, Fabricated by SHS, Combining Strong and Weak Exothermic Reactions,” *Materials (Basel)*, **6** [5] 1903–1919 (2013).
- ³ K.B. Panda and K.S. Ravi Chandran, “Determination of elastic constants of titanium diboride (TiB₂) from first principles using FLAPW implementation of the density functional theory,” *Comput. Mater. Sci.*, **35** [2] 134–150 (2006).
- ⁴ S.P. Ray, “Boride-alumina composites,” *Metall. Trans. A*, **23** [9] 2381–2385 (1992).
- ⁵ R.A. Cutler, “Engineering properties of borides,” pp. 787–801 in *Eng. Mater. Handbook, Vol. 4*. ASM International, Metals Park, Ohio, 1991.
- ⁶ Y.-M. Chiang, D.P. Birnie, and W.D. Kingery, *Physical Ceramics: Principles for Ceramic Science and Engineering*. John Wiley & Sons, New York, 1997.
- ⁷ R. Telle, “Boride and carbide ceramics,” p. 175 in *Mater. Sci. Technol.* Edited by R.W. Cahn. VCH, Weinheim, 1994.
- ⁸ G. Goor, P. Sagesser, and K. Berroth, “Electrically conductive ceramic composites,” *Solid State Ionics*, **101** [103] 1163–1170 (1997).
- ⁹ J. Li, X. Lü, Y. Lai, Q. Li, and Y. Liu, “Research Progress in TiB₂ Wettable Cathode for Aluminum Reduction,” *JOM*, **60** [8] 32–37 (2008).
- ¹⁰ P.S. Mohanty and J.E. Gruzleskit, “Mechanism of grain refinement in aluminum,” *Pergamon*, **43** [5] 2001–2012 (1995).

- 11 S.G. Huang, K. Vanmeensel, O.J. a. Malek, O. Van der Biest, and J. Vleugels, "Microstructure and mechanical properties of pulsed electric current sintered B₄C–TiB₂ composites," *Mater. Sci. Eng. A*, **528** [3] 1302–1309 (2011).
- 12 A. Kulpa and T. Troczynski, "Oxidation of TiB₂ Powders below 900 °C," *J. Am. Ceram. Soc.*, **79** [2] 518–520 (1996).
- 13 S. Baik and P.F. Becher, "Effect of Oxygen Contamination on Densification of TiB₂," *J. Am. Ceram. Soc.*, **70** [8] 527–530 (1987).
- 14 L. Ferranti and N.N. Thadhani, "Quantitative Characterization of the Microstructure of Two-Phase TiB₂ + Al₂O₃ Ceramics Using Mean Integral Curvature," *Metall. Mater. Trans. A*, **34A** [November] 2671–2678 (2003).
- 15 G. Suskin and G. Chepovetsky, "Comparison of vacuum and pressure assisted sintering of TiB₂–Ni," *J. Mater. Eng. Perform.*, **5** 396–398 (1996).
- 16 S. Torizuka and T. Kishi, "Effect of SiC and ZrO₂ on sinterability and mechanical properties of titanium nitride, titanium carbonitride, and titanium diboride," *Mater. Trans.*, **37** 782–787 (1996).
- 17 S. Torizuka, H. Nishio, and T. Kishi, "Sinterability and mechanical properties of TiB₂ without additives," *J. Ceram. Soc. Japaneramic Soc. Japan*, **103** 1077–1081 (1995).
- 18 J. Matsushita, H. Nagashima, and H. Saito, "Preparation and mechanical properties of TiB₂ composites containing Ni and C," *J. Ceram. Soc. Japan*, **99** 78–82 (1991).
- 19 M. Einarsrud, E. Hagen, G. Pettersen, and T. Grande, "Pressureless sintering of titanium diboride with nickel, nickel boride, and iron additives," *J. Am. Ceram. Soc.*, **80** 3013–3020 (1997).
- 20 V.J. Tennery, C.B. Finch, C.S. Yust, and G.W. Clark, "Structure-Property Correlations for TiB₂ Based Ceramics Densified Using Active Liquid Metals," pp. 891–909 in *Sci. Hard Mater.* Edited by R.K. Viswanadham, D.J. Rowcliffe and J. Gurland. Plenum, New York, 1981.
- 21 C.E. Holcombe and N.L. Dykes, "Microwave sintering of titanium diboride," *J. Mater. Sci.*, **26** [14] 3730–3738 (1991).
- 22 J. Besson, F. Valin, P. Lointier, and M. Boncoeur, "Densification of titanium diboride by hot isostatic pressing and production of near-net-shape components," *J. Mater. Eng. Perform.*, **1** 637–650 (1992).
- 23 Y. Muraoka, M. Yoshinaka, K. Hirota, and O. Yamaguchi, "Hot isostatic pressing of TiB₂–ZrO₂ (2 mol% Y₂O₃) composite powders," *Mater. Res. Bull.*, **31** 787–792 (1996).

- 24 L. Wang and M.R. Wixom, "Structural and mechanical properties of TiB₂ and TiC prepared by self-propagating high-temperature synthesis/dynamic compaction," *J. Mater. Sci.*, **29** 534–543 (1994).
- 25 E. Rudy, *Ternary phase equilibria in transition metal-boron-carbon-silicon systems*. Ohio, 1969.
- 26 A.E. McHale, *Phase equilibria diagrams, Vol. X, Borides, Carbides, and Nitrides*. American Ceramic Society, 1994.
- 27 H. Duschaneck, P. Rogl, and H.L. Lukas, "A critical assessment and thermodynamic calculation of the boron-carbon-titanium (B-C-Ti) ternary system," *J. Phase Equilibria*, **16** [1] 46–60 (1995).
- 28 G.B. Raju, "Development of high temperature TiB₂ based ceramics," *Key Eng. Mater.*, **395** 89–124 (2009).
- 29 P.C. Cobb, "Titanium carbide as a sintering agent for titanium boride," *Mater. Des.*, **11** [3] 156–159 (1990).
- 30 J. Matsushita and A. Sano, "Sinterability of TiB₂ ceramics containing Cr and C as the sintering aids," *J. Ceram. Soc. Japan/Ceram. Soc. Japan*, **100** [4] 593–595 (1992).
- 31 M. Cologna, B. Rashkova, and R. Raj, "Flash sintering of nanograin zirconia in <5 s at 850°C," *J. Am. Ceram. Soc.*, **93** [11] 3556–3559 (2010).
- 32 E.K. Akdoğan, I. Şavklıyıldız, H. Biçer, W. Paxton, F. Toksoy, Z. Zhong, and T. Tsakalakos, "Anomalous lattice expansion in yttria stabilized zirconia under simultaneous applied electric and thermal fields: A time-resolved in situ energy dispersive x-ray diffractometry study with an ultrahigh energy synchrotron probe," *J. Appl. Phys.*, **113** [23] 233503 (2013).
- 33 S. Grasso, C. Hu, G. Maizza, B.-N. Kim, and Y. Sakka, "Effects of pressure application method on transparency of spark plasma sintered alumina," *J. Am. Ceram. Soc.*, **94** [5] 1405–1409 (2011).
- 34 H. Conrad and D. Yang, "Influence of an applied dc electric field on the plastic deformation kinetics of oxide ceramics," *Philos. Mag.*, **90** [9] 1141–1157 (2010).
- 35 X. Hao, Y. Liu, Z. Wang, J. Qiao, and K. Sun, "A novel sintering method to obtain fully dense gadolinia doped ceria by applying a direct current," *J. Power Sources*, **210** 86–91 (2012).
- 36 H. Biçer, E.K. Akdoğan, B. Visser, I. Savklıyıldız, T.E. Ozdemir, Z. Zhong, and T. Tsakalakos, "Insitu time resolved EDXRD on densification of B₄C under superimposed electric and thermal fields at ultralow temperatures," *Unpubl. data*, (2015).

- 37 R. Raj, "Joule heating during flash-sintering," *J. Eur. Ceram. Soc.*, **32** [10] 2293–2301 (2012).
- 38 T. Graziani, E. Landi, and A. Bellosi, "Oxidation of TiB₂-20 vol% B₄C composite," *J. Mater. Sci. Lett.*, **12** 691–694 (1993).
- 39 A. Tampieri and A. Bellosi, "Oxidation of monolithic TiB₂ and of Al₂O₃-TiB₂ composite," *J. Mater. Sci.*, **28** 649–653 (1993).
- 40 R.J. Irving and I.G. Worsley, "The oxidation of titanium diboride and zirconium diboride at high temperatures," *J. Less Common Met.*, **16** 103–112 (1968).
- 41 Y. Koh, S. Lee, and H. Kim, "Oxidation Behavior of Titanium Boride at Elevated Temperatures," *J. Am. Ceram. Soc.*, **41** 239–241 (2001).
- 42 D.B. Lee, M.H. Kim, C.W. Yang, S.H. Lee, M.H. Yang, and Y.J. Kim, "The Oxidation of TiB₂ Particle-Reinforced TiAl Intermetallic Composites," *Oxid. Met.*, **56** [3/4] 215–229 (2001).
- 43 D.B. Lee, Y.C. Lee, and D.J. Kim, "The Oxidation of TiB₂ Ceramics Containing Cr and Fe," *Oxid. Met.*, **56** [1/2] 177–189 (2001).
- 44 L. Li, D.J. Weidner, J. Chen, M.T. Vaughan, and M. Davis, "X-ray strain analysis at high pressure: Effect of plastic deformation in MgO," *J. Appl. Phys.*, **95** [12] 8357–8365 (2004).
- 45 Y. Wang, W.B. Durham, I.C. Getting, and D.J. Weidner, "The deformation-DIA: A new apparatus for high temperature triaxial deformation to pressures up to 15 GPa," *Rev. Sci. Instrum.*, **74** [6] 3002–3011 (2003).
- 46 J.C.H. Spence, N.A. Zatsepin, and C. Li, "Coherent convergent-beam time-resolved X-ray diffraction," *Philos. Trans. R. Soc. Lond. B. Biol. Sci.*, **369** [1647] 20130325 (2014).
- 47 A. Steuwer, J.R. Santisteban, M. Turski, P.J. Withers, and T. Buslaps, "High-resolution strain mapping in bulk samples using full-profile analysis of energy dispersive synchrotron X-ray diffraction data," *Nucl. Instruments Methods Phys. Res. Sect. B Beam Interact. with Mater. Atoms*, **238** 200–204 (2005).
- 48 US Research Nanomaterials Inc., *Titanium diboride nanopowder/nanoparticles (95+%, 58nm, hexagonal)*, (2014).
- 49 O. Kubaschewski, "Titanium: Pyysico-Chemical Properties of its Compounds and Alloys," in *Int. At. Agency*. Edited by K.L. Komarek. Vienna, 1983.

- 50 J.H. Holtz, J.S.W. Holtz, C.H. Munro, and S.A. Asher, "Intelligent polymerized crystalline colloidal arrays : Novel chemical sensor materials," *Anal. Chem.*, **70** [4] 780–791 (1998).
- 51 A. Pais, "Einstein and the quantum theory," *Rev. Mod. Phys.*, **51** [4] 863–914 (1979).
- 52 E.K. Akdoğan, I. Savkliyildiz, Z. Zhong, and T. Tsakalakos, "Line profile calibration of ultrahigh energy synchrotron EDXRD data by LaB6," *Unpubl. data*, (2013).
- 53 M.I. Aivazov and I.A. Domashev, "Electrophysical properties of titanium diboride and alloys in the system Ti-B-N," *Inorg. Mater.*, **7** 1551–1553 (1971).
- 54 W.H. Baur and A.A. Khan, "Rutile-type compounds. IV. SiO₂, GeO₂ and a comparison with other rutile-type structures," *Acta Crystallogr. Sect. B Struct. Crystallogr. Cryst. Chem.*, **B27** 2133–2139 (1971).
- 55 M. Huber and H.J. Deiseroth, "Crystal structure of titanium (III) borate, TiBO₃," *Zeitschrift für Krist.*, **210** [9] 685 (1995).
- 56 R.P. Feynman, R.B. Leighton, and M. Sands, *The Feynman lectures on physics: Electromagnetism and matter*. Addison-Wesley, 1964.
- 57 J. Park, Y. Lee, Y. Koh, and H. Kim, "Effect of hot-pressing temperature on densification and mechanical properties of titanium diboride with silicon nitride as a sintering aid," *J. Am. Ceram. Soc.*, **83** [6] 1542–1544 (2000).
- 58 T. Graziani, E. Landi, and A. Bellosi, "Oxidation of TiB₂-20 vol % B₄C composite," *J. Mater. Sci. Lett.*, **12** [10] 691–694 (1993).
- 59 A. Tampieri and A. Bellosi, "Oxidation of monolithic TiB₂ and of Al₂O₃-TiB₂ composite," *J. Mater. Sci.*, **28** [3] 649–653 (1993).
- 60 R.J. Irving and I.G. Worsley, "The oxidation of titanium diboride and zirconium diboride at high temperatures," *J. Less Common Met.*, **16** [2] 103–112 (1968).